

3 August 2026 | ASX: SLS

Multiple Wide >1% Cu Intercepts Continue to Grow Nanadie Copper-Gold System

Highlights

- Ongoing Reverse Circulation (RC) drilling at the 100%-owned **Nanadie Copper-Gold Project**, located in the Goldfields of Western Australia, has delivered **more wide zones of significant copper mineralisation**, continuing to extend the mineralisation well beyond the current Mineral Resource Estimate (MRE).
- **Nine of the ten RC holes** reported in this announcement delivered **significant intercepts**, with standout results including:
 - ❖ **51m @ 1.03% Cu, 0.29g/t Au** from 194m and **33m @ 0.43% Cu, 0.07g/t Au** from 62m in NANRC041.
 - ❖ **97m @ 0.57% Cu, 0.16g/t Au** from 173m in NANRC038.
 - ❖ **30m @ 1.15% Cu, 0.25g/t Au** from 240m and **21m @ 0.57% Cu, 0.21g/t Au** from 281m in NANRC035.
 - ❖ **35m @ 0.87% Cu, 0.27g/t Au** from 144m, including **12m @ 1.38% Cu, 0.49g/t Au** from 163m in NANRC040.
 - ❖ **37m @ 0.40% Cu, 0.11g/t Au** from 278m and **18m @ 0.56% Cu, 0.14g/t Au** from 322m to end of hole (EOH) in NANRC037.
- Most drillholes were completed as 'pre-collars' for extending via future diamond 'tails'. Importantly, the **widespread mineralisation** intersected in the pre-collar component **further demonstrates the width of the overall mineralised system**.
- Wide zones of mineralisation continue to take shape over a **strike length of approximately 1.2km**, including **multiple zones of high-grade mineralisation** associated with alteration and deformation in the eastern 100m of the host gabbro body.
- **Assay results are pending** for **12 diamond 'tails'** and over **30 RC holes** completed along the length of the mineralised system.
- Recent assays from the first diamond tail, **NANRCD004**, delivered an exceptional combined RC and diamond intercept of **629.1m @ 0.50% Cu, 0.17g/t Au** from surface to end of hole (EOH)¹ (including all unmineralised intervals), as well as **multiple >1% Cu zones downhole**.
- **Solstice's drilling is demonstrating clear potential to materially expand** the current shallow MRE of **40.4Mt** containing 162,000t of copper and 130,000oz of gold² within a large **granted Mining Lease**.



- **RC and diamond drilling continues to test depth, strike and lateral extensions** throughout the mineralised footprint, with observed geology broadly consistent with Solstice's releases to date. The RC component of the program comprises step-out exploration tests, MRE delineation holes, and 'pre-collar' holes designated for future diamond tails.

Solstice Minerals' Chief Executive Officer and Managing Director, Mr Nick Castleden, said:

"Our ongoing >15,000m RC drilling campaign continues to strengthen our belief that Nanadie is emerging as one of Australia's more significant undeveloped copper-gold systems. Every new batch of drill results reveals a much larger copper-gold system than previously recognised, remaining open at both ends and at depth.

"Importantly, nine of the ten RC holes reported today intersected widespread mineralisation and significant grade positions, despite mostly being drilled as pre-collars for deeper diamond holes. The eastern side of the gabbro host package is continuing to emerge as a higher-grade corridor with intercepts in this batch of holes often beyond the current MRE boundary or demonstrating higher-than-modelled copper-gold grades – observations that will be important in future Mineral Resource work. A number of holes ended in mineralised host gabbro and will be immediately extended by diamond drilling.

"Like much of the industry, we continue to experience slower laboratory turnaround times. While frustrating, drilling continues to make excellent progress, and we have a substantial pipeline of assay results still to come. We eagerly await results from our remaining diamond tails, particularly the follow-up diamond hole NANRCD005, which is interpreted to extend the mineralised host geology approximately 500m below the MRE boundary.

"The combined RC and diamond drilling campaign continues to scope out mineralisation well beyond the current MRE boundary, with observed geology consistent with that reported to date. With assays pending from over 40 RC and diamond holes, we believe Nanadie is emerging as a significant and strategic Australian copper-gold system with the benefit of granted mining tenure in a favourable WA Goldfields location. With approximately \$45 million in cash and no debt, Solstice is well funded to continue systematically growing Nanadie. We have multiple rigs operating and a growing pipeline of high-priority targets with potential to further expand this open-ended high-volume system with the goal of materially expanding the MRE over time."

Nanadie RC Update

Solstice Minerals Limited (**Solstice** or the **Company**) is pleased to report **continued strong assay results** from its ongoing **Reverse Circulation (RC) drilling** at the advanced 100%-owned **Nanadie Copper-Gold Project**, located northwest of Sandstone in WA's Goldfields.

RC drilling has delivered **multiple wide zones of significant copper mineralisation** in holes that were mostly drilled as 'pre-collars' for extending with future diamond 'tails' (i.e. the key target zone remains further to the east/at depth). Importantly, **nine of the ten RC holes** reported here intersected **widespread disseminated and vein style chalcopyrite (copper sulphide) mineralisation** in the pre-collar component of these holes, **further demonstrating the width of**



the host gabbro and of the overall mineralised system. The deposit as currently defined is 100-200m wide, at least 1.2km long, and remains open to the north, south and at depth (Figure 1).




Figure 1. Nanadie Deposit aeromagnetic imagery and downhole copper values in previous drilling projected to surface showing the location of RC drillholes and selected intercepts reported in this release, drillholes extended with diamond tails (labelled), and all completed and planned RC drill collars in the current program (blue dots)^{1,2,3,4}.

Standout RC intercepts are summarised in Figure 1 and include:

- ❖ **51m @ 1.03% Cu, 0.29g/t Au** from 194m and **33m @ 0.43% Cu, 0.07g/t Au** from 62m in NANRC041 (Figure 2).
- ❖ **97m @ 0.57% Cu, 0.16g/t Au** from 173m in NANRC038 (Figure 3).
- ❖ **30m @ 1.15% Cu, 0.25g/t Au** from 240m and **21m @ 0.57% Cu, 0.21g/t Au** from 281m in NANRC035, within a broader combined anomalous intercept of **231m @ 0.36% Cu, 0.11g/t Au** (Figure 4).
- ❖ **35m @ 0.87% Cu, 0.27g/t Au** from 144m including **12m @ 1.38% Cu, 0.49g/t Au** from 163m in NANRC040.



- ❖ **37m @ 0.40% Cu, 0.11g/t Au** from 278m and **18m @ 0.56% Cu, 0.14g/t Au** from 322m to end of hole (EOH) in NANRC037.
- ❖ **36m @ 0.55% Cu, 0.16g/t Au** from 176m, 12m @ 0.59% Cu, 0.18g/t Au from 278m, and 10m @ 0.59% Cu, 0.12g/t Au from 115m in NANRC033.
- ❖ **29m @ 0.43% Cu, 0.17g/t Au** from 47m, **16m @ 0.63% Cu, 0.19g/t Au** from 130m, **6m @ 1.63% Cu, 0.54g/t Au** from 168m, and 13m @ 0.59% Cu, 0.22g/t Au to EOH in NANRC034.
- ❖ **26m @ 0.43% Cu, 0.13g/t Au** from 125m in NANRC036.

Broad and continuous zones of mineralisation continue to take shape over a strike length of approximately 1.2km, including multiple zones of high-grade mineralisation associated with alteration and deformation in the eastern 100m of the host gabbro (**Figure 2**). This **'eastern margin' corridor is emerging as a key exploration and MRE extension target** that will see a combination of shallow RC drilling and diamond tails over the coming months to increase drill density through the zone.

Recent assays from the Company's first diamond tail, NANRCD004, delivered an exceptional combined RC and diamond intercept of **629.1m @ 0.50% Cu, 0.17g/t Au** from surface to end of hole (EOH)¹ (including all unmineralised intervals), including **62m @ 1.55% Cu, 0.66g/t Au, 30.7m @ 1.41% Cu, 0.34g/t Au** and **37.8m @ 0.87% Cu, 0.25g/t Au** all within the eastern margin of the host gabbro. Visual observations of **significant disseminated and vein sulphide** were also reported in follow-up tail **NANRCD005**³, which intersected strong zones of mineralisation from the base of the pre-collar to its final depth of 840m.

Importantly, **assays are pending for NANRCD005** and a further **11 diamond 'tails' (Figure 5)** as well as over **30 additional RC holes**, which will add to Solstice's understanding of the growing mineralised system.




Figure 2. Nanadie Project cross-section 6994840N showing RC drillhole NANRC0041, previous drilling, and simplified geology^{1,2,3,4}.




Figure 3. Nanadie Project cross-section 6994680N showing RC drillholes NANRC0038 and NANRC0039, previous drilling, and simplified geology^{1,2,3,4}.



Solstice's ongoing >15,000m RC campaign comprises step-out strike traverses, MRE delineation holes, and 'pre-collar' holes designated for future diamond tails and is generally testing the deposit between surface and approximately 300m downhole, which is the typical operating capacity of the RC drilling technique in this area.

Observed geology in both RC and diamond drilling continues to be broadly consistent with that seen in Solstice's Phase 1 drilling and is building the Company's geological understanding of this substantial and growing mineralised system.

All significant assay results are shown on **Figure 1**, and in **Table 1**. All individual analytical results above 0.10% Cu are shown in **Table 3**.




Figure 4. Nanadie Project cross-section 6994540N showing RC drillhole NANRC0035, previous drilling, and simplified geology^{1,2,3,4}.




Figure 5. Nanadie long section looking west, showing all diamond tails with assays pending, (blue) and RC drill traces (black) relative to historical drilling and the maximum extent the 2022 MRE area. Key Phase 1 RC and NANRCD004 intercepts, 2025 IP chargeability anomalies also shown^{1,2,3,4,5}.

Table 1. Nanadie Phase 2 RC program - all completed RC drillhole details and significant assay results this release (10m downhole length @ >0.40% Cu).

Hole ID	Prospect	Type	Easting	Northing	RL	Dip	Azim	Depth	Significant Intercepts	From
NANRC033	Nanadie	RC	692939	6994748	475	-60	90	321	10m @ 0.59% Cu, 0.12 g/t Au	115.0
								and	36m @ 0.55% Cu, 0.16g/t Au	176.0
								and	12m @ 0.59% Cu, 0.18 g/t Au	278.0
NANRC034	Nanadie	RC	693000	6994440	475	-60	90	258	29m @ 0.43% Cu, 0.17g/t Au	47.0
								and	14m @ 0.56% Cu, 0.18 g/t Au	100.0
								and	16m @ 0.63% Cu, 0.19 g/t Au	130.0
								and	6m @ 1.63% Cu, 0.54 g/t Au	168.0
								and	13m @ 0.59% Cu, 0.22 g/t Au EOH	245.0
NANRC035	Nanadie	RC	692895	6994562	475	-60	90	330	14m @ 0.53% Cu, 0.09g/t Au	132.0
								and	13m @ 0.42% Cu, 0.15g/t Au	199.0
								and	30m @ 1.15% Cu, 0.25 g/t Au	240.0
								and	21m @ 0.57% Cu, 0.21 g/t Au	281.0
								and	10m @ 0.76% Cu, 0.18g/t Au	308.0
NANRC036	Nanadie	RC	693057	6994402	475	-60	90	268	26m @ 0.43% Cu, 0.13g/t Au	125.0
NANRC037	Nanadie	RC	692852	6994406	475	-60	90	340	37m @ 0.40% Cu, 0.11g/t Au	278.0
								and	18m @ 0.56% Cu, 0.14 g/t Au EOH	322.0
NANRC038	Nanadie	RC	692967	6994681	475	-60	90	328	97m @ 0.57% Cu, 0.16g/t Au	173.0
NANRC039	Nanadie	RC	692869	6994683	475	-60	90	316	11m @ 0.56% Cu, 0.11g/t Au	232.0
								and	21m @ 0.40% Cu, 0.13 g/t Au EOH	296.0
NANRC040	Nanadie	RC	692967	6994802	475	-60	90	232	16m @ 0.41% Cu, 0.04g/t Au	116.0
									35m @ 0.87% Cu, 0.27g/t Au	144.0
								including	12m @ 1.38% Cu, 0.49g/t Au	163.0
NANRC041	Nanadie	RC	692897	6994844	475	-60	90	304	33m @ 0.43% Cu, 0.07g/t Au	62.0
									51m @ 1.03% Cu, 0.29g/t Au	194.0
NANRC042	Nanadie	RC	692840	6994600	475	-60	90	200	NSR (pre-collar)	



Significant intercepts in Table 1 are reported at a minimum 10m interval at >0.4% Cu, on the basis of a 0.2% Cu and 0.1g/t Au lower cut-off and allowing for a maximum 5m internal dilution.

Nanadie Results Summary

Results from Solstice's continuing RC and diamond drilling have clearly extended mineralisation in multiple directions well beyond the current MRE boundary and are demonstrating clear potential to expand an already significant deposit into a **standout large-volume copper-gold system in WA's premier Goldfields mining jurisdiction**.

Batches of RC assay results are expected throughout 2H 2026.

With \$45 million cash and no debt, Solstice is well positioned to continue growing Nanadie through drilling, IP and downhole EM geophysical techniques, and applying an updated geological model that has opened targets at the nearby **Stark Prospect** and exploration corridors extending north from Nanadie and Stark beneath shallow transported cover

About the Nanadie Copper Gold Deposit

Nanadie is situated within a granted Mining Lease approximately 100km northwest of Sandstone (**Figure 6**) and includes an existing Inferred MRE of **40.4 million tonnes at 0.4% copper and 0.1g/t gold**, containing **162,000 tonnes of copper** and **130,000 ounces of gold¹** (**Table 3**). The deposit represents a substantial base of strategic metals with strong future demand outlooks.

Historical drilling below a shallow soil and sand cover and weathering profile has defined wide, near-surface zones of disseminated and remobilised sulphide veinlet style chalcopyrite (+/- pyrrhotite and pyrite) mineralisation in a gabbro unit 100m-200m wide and at least 1.2 km long. Approximately 90% of the current MRE is in fresh rock below a shallow (less than 40m) weathering profile. Significant zones of >1% Cu occur where chalcopyrite vein density and host-rock alteration increases, and increased sulphide veining is typically accompanied by raised gold values. No deleterious sulphide species are present.

Solstice's updated geological model suggests that Nanadie and the nearby Stark Prospect are broad accumulations of primary disseminated copper-gold sulphide mineralisation that has been remobilised in places during a subsequent felsic intrusion, deformation and alteration event. The secondary event is likely responsible for the wide zones of high-grade mineralisation encountered to date.



Table 2. Nanadie Well 2012 JORC Mineral Resource Estimate².

Resource Category	Material Type	Volume	Tonnes	Cu Grade (%)	Cu Metal (t)	Au Grade (g/t)	Au Metal (oz)	Ag Grade (g/t)	Ag Metal (oz)
Inferred	Oxide	1,300,000	3,500,000	0.44	16,000	0.12	13,000	0.70	74,000
	Transitional	200,000	600,000	0.45	3,000	0.12	2,000	1.50	31,000
	Fresh	11,700,000	36,300,000	0.39	143,000	0.10	115,000	1.10	1,259,000
Total		13,200,000	40,400,000	0.4	162,000	0.10	130,000	1.00	1,364,000

Note: Differences in sum totals of tonnages and grades may occur due to rounding cut-off at 0.25% Cu, reported grades and tonnages for all metals are estimated top-cut grades and tonnages.



Photo 1. Typical RC drill samples (NANRC001) at Nanadie². Note the limited oxidation profile below shallow sandy soils.

References

1. For initial diamond drilling results at Nanadie Copper-Gold Project refer to ASX: SLS 26 June 2026 'Exceptional Wide Copper-Gold Intercepts in First Diamond Hole at Nanadie'
2. For historical drill intercepts and current estimates of mineral resources from the Nanadie Copper-Gold Project refer to ASX: SLS 5 February 2025 'Solstice Secures Strategic Copper Exposure'.
3. Refer to ASX: SLS 27 April 2026 'Strong Start to Diamond Drilling at Nanadie Copper-Gold Project, WA', and ASX: SLS 11 May 2026 "Strong Zones in Follow-up Diamond Drillhole at Nanadie".
4. For all prior Phase 1 and Phase 2 RC drilling results at Nanadie Copper-Gold Project refer to ASX: SLS 3 February 2026 'Outstanding High-Grade Cu-Au Intercepts at Nanadie', 23 February 2026 'Strong Copper-Gold Intercepts Continue at Nanadie Project', 3 March 2026 'New High-Grade Zone Emerges at Nanadie Copper-Gold Project', 17 March 2026 'Significant Copper-Gold Growth Potential at



Nanadie Project' and 12 June 2026 'Step-Out RC Drilling Extends Nanadie Copper-Gold Mineralisation Beyond Resource Boundary'.

- For previous IP survey results refer to ASX: SLS 8 August 2025 'IP Survey Points to Step-Out Drill Targets at Nanadie Copper Gold Project'.

All exploration releases are available on the Company's website at:

<https://solsticeminerals.com.au/investor-centre/asx-announcements>.

This announcement has been authorised for release by the Board.

For further information please contact:
Nick Castleden - CEO & Managing Director
T: +61 (8) 9200 1838

Media inquiries:
Nicholas Read - Read Corporate
T: +61 (8) 9388 1474




Figure 6. Location of the Nanadie Copper-Gold Project tenements NW of Sandstone WA.

Forward-Looking Statements

This announcement may contain certain forward-looking statements, guidance, forecasts, estimates, prospects, projections or statements in relation to future matters that may involve risks or uncertainties and may involve significant items of subjective judgement and assumptions of future events that may or may not eventuate (**Forward-Looking Statements**). Forward-Looking Statements can generally be identified by the use of forward-looking words such as "anticipate", "estimates", "will", "should", "could", "may", "expects", "plans", "forecast", "target" or similar expressions and may include, without limitation, statements regarding plans, strategies and objectives of management, anticipated production and expected costs. Indications of, and guidance on future earnings, cash flows, costs, financial position and performance are also Forward-Looking Statements.

Persons reading this announcement are cautioned that such statements are only predictions, and that actual future results or performance may be materially different. Forward-Looking Statements, opinions and estimates included in this announcement are based on assumptions and contingencies which are subject to change, without notice, as are statements about market and industry trends, which are based on interpretation of current market conditions. Forward-Looking Statements are provided as a general guide only and should not be relied on as a guarantee of future performance.

No representation or warranty, express or implied, is made by Solstice that any Forward-Looking Statement will be achieved or proved to be correct. Further, Solstice disclaims any intent or obligation to update or revise any Forward-Looking Statement whether as a result of new information, estimates or options, future events or results or otherwise, unless required to do so by law.

Compliance Statement - New Results

The information in this release that relates to new Exploration Results is based on and fairly represents information and supporting documentation prepared by Mr Nick Castleden, a competent person who is a Member of the Australian Institute of Geoscientists. Mr Castleden is an employee of Solstice Minerals Limited. Mr Castleden has sufficient experience that is relevant to the style of mineralisation and type of deposits under consideration and to the activity which he is undertaking to qualify as a Competent Person as defined in the 2012 Edition of the 'Australasian Code for Reporting of Exploration Results, Mineral Resources and Ore Reserves'. Mr Castleden consents to the inclusion in this release of the new Exploration Results in the form and context in which they appear.

Compliance Statement - Previously Reported Results

The information in this announcement that relates to previously reported Exploration Results and Estimates of Mineral Resources is extracted from the ASX announcements as noted in the 'References' and referenced in the text (**Original Announcements**). The Company confirms that it is not aware of any new information or data that materially affects the relevant information included in the Original Announcements and, in the case of Estimates of Mineral Resources, that all material assumptions and technical parameters underpinning the estimates in the Original Announcements continue to apply and have not materially changed. Solstice confirms that the form and context in which the Competent Persons' findings are presented have not been materially modified from the Original Announcement.

**Table 3. All individual analytical results above 0.10% Cu**

Hole ID	FROM (m)	TO (m)	Cu (%)	Au (g/t)	Ag (g/t)
NANRC033	66	67	0.16	0.06	0.91
NANRC033	67	68	0.24	0.08	0.66
NANRC033	68	69	0.18	0.06	0.51
NANRC033	69	70	0.35	0.13	1.27
NANRC033	84	85	0.26	X	0.64
NANRC033	85	86	0.20	X	0.67
NANRC033	86	87	0.14	X	0.45
NANRC033	87	88	0.40	0.01	1.24
NANRC033	88	89	0.41	0.01	1.68
NANRC033	89	90	0.26	0.01	1.29
NANRC033	90	91	0.15	X	0.56
NANRC033	91	92	0.65	0.01	1.34
NANRC033	95	96	0.14	X	0.45
NANRC033	96	97	0.12	0.01	1.44
NANRC033	97	98	0.13	X	0.72
NANRC033	101	102	1.29	0.05	5.29
NANRC033	102	103	1.63	0.05	5.66
NANRC033	103	104	0.33	0.01	1.31
NANRC033	115	116	0.73	0.25	2.84
NANRC033	116	117	1.95	0.41	8.16
NANRC033	117	118	0.20	0.02	0.79
NANRC033	118	119	0.47	0.12	1.81
NANRC033	119	120	0.14	0.01	0.54
NANRC033	120	121	0.39	0.11	1.05
NANRC033	121	122	0.48	0.07	1.3
NANRC033	122	123	0.48	0.08	1.41
NANRC033	123	124	0.37	0.08	0.97
NANRC033	124	125	0.67	0.11	1.51
NANRC033	130	131	0.31	0.07	0.79
NANRC033	131	132	0.33	0.06	0.83
NANRC033	132	133	0.26	0.10	0.55
NANRC033	133	134	0.35	0.12	0.8
NANRC033	134	135	0.17	0.06	0.34
NANRC033	135	136	0.11	0.01	0.31
NANRC033	137	138	0.18	0.04	0.52
NANRC033	138	139	0.30	0.12	0.65
NANRC033	139	140	0.11	0.03	0.24
NANRC033	140	141	0.19	0.06	0.42
NANRC033	143	144	0.26	0.13	0.45
NANRC033	144	145	0.20	0.15	0.34
NANRC033	145	146	0.14	0.08	0.22
NANRC033	148	149	0.12	0.03	0.32
NANRC033	149	150	0.14	0.03	0.54
NANRC033	150	151	0.25	0.12	0.77
NANRC033	151	152	0.42	0.13	1.06
NANRC033	152	153	1.44	0.33	3.73
NANRC033	153	154	0.15	0.04	0.33
NANRC033	154	155	0.17	0.07	0.3
NANRC033	155	156	0.10	0.04	0.25
NANRC033	157	158	0.30	0.06	1
NANRC033	158	159	0.36	0.07	1.06
NANRC033	159	160	0.55	0.13	1.56
NANRC033	162	163	0.45	0.18	1.03
NANRC033	163	164	0.27	0.12	0.57
NANRC033	164	165	0.55	0.14	1.3
NANRC033	165	166	0.51	0.08	1.43
NANRC033	166	167	0.36	0.11	0.93
NANRC033	167	168	0.51	0.14	2.58
NANRC033	174	175	0.13	0.02	0.35

Hole ID	FROM (m)	TO (m)	Cu (%)	Au (g/t)	Ag (g/t)
NANRC033	175	176	0.11	0.02	0.27
NANRC033	176	177	1.31	0.31	3.12
NANRC033	177	178	0.30	0.09	0.73
NANRC033	178	179	0.40	0.08	1.09
NANRC033	180	181	0.32	0.11	0.64
NANRC033	181	182	0.28	0.09	0.47
NANRC033	182	183	0.43	0.19	0.74
NANRC033	183	184	0.47	0.14	0.89
NANRC033	184	185	0.57	0.17	0.98
NANRC033	185	186	0.54	0.19	0.95
NANRC033	186	187	0.60	0.22	1.02
NANRC033	187	188	0.33	0.12	0.6
NANRC033	188	189	0.41	0.16	0.75
NANRC033	189	190	0.98	0.17	2
NANRC033	190	191	0.54	0.15	1
NANRC033	191	192	0.88	0.16	1.7
NANRC033	194	195	0.50	0.16	0.94
NANRC033	195	196	0.70	0.20	1.68
NANRC033	196	197	0.85	0.30	1.88
NANRC033	197	198	0.43	0.04	1.52
NANRC033	198	199	0.34	0.05	1.4
NANRC033	199	200	1.05	0.26	2.91
NANRC033	200	201	0.58	0.84	1.42
NANRC033	201	202	1.80	0.33	3.98
NANRC033	202	203	1.11	0.20	2.57
NANRC033	203	204	0.96	0.22	2.05
NANRC033	204	205	0.54	0.14	1.26
NANRC033	208	209	0.19	0.07	0.37
NANRC033	209	210	0.82	0.22	1.47
NANRC033	210	211	0.90	0.09	2.02
NANRC033	211	212	0.66	0.13	1.83
NANRC033	224	225	0.29	0.08	0.49
NANRC033	225	226	0.81	0.18	1.4
NANRC033	226	227	0.23	0.07	0.4
NANRC033	227	228	0.45	0.12	0.75
NANRC033	228	229	0.57	0.40	1.01
NANRC033	229	230	0.20	0.07	0.71
NANRC033	230	231	0.22	0.08	0.39
NANRC033	242	243	0.28	0.09	0.75
NANRC033	243	244	0.15	0.04	0.26
NANRC033	244	245	0.23	0.06	0.38
NANRC033	245	246	0.18	0.06	0.3
NANRC033	257	258	0.27	0.10	0.47
NANRC033	258	259	0.25	0.10	0.44
NANRC033	278	279	0.38	0.18	0.72
NANRC033	279	280	1.07	0.27	2.44
NANRC033	280	281	0.63	0.16	1.46
NANRC033	281	282	0.65	0.19	1.44
NANRC033	282	283	1.00	0.35	2.18
NANRC033	283	284	0.63	0.16	1.47
NANRC033	284	285	0.80	0.25	1.81
NANRC033	285	286	0.66	0.16	1.49
NANRC033	286	287	0.21	0.06	0.52
NANRC033	287	288	0.44	0.24	1.1
NANRC033	288	289	0.36	0.07	2.17
NANRC033	290	291	0.24	0.07	1.92
NANRC033	301	302	0.25	0.02	1.21
NANRC033	302	303	0.43	0.18	1.48
NANRC033	303	304	0.79	0.22	2.35



Hole ID	FROM (m)	TO (m)	Cu (%)	Au (g/t)	Ag (g/t)
NANRC033	304	305	0.30	0.12	0.83
NANRC033	305	306	0.18	0.06	0.45
NANRC033	306	307	0.21	0.08	0.42
NANRC033	307	308	0.18	0.07	0.36
NANRC033	309	310	0.13	0.05	0.27
NANRC033	310	311	0.16	0.09	0.33
NANRC034	7	8	0.10	0.06	0.35
NANRC034	8	9	0.13	0.02	0.33
NANRC034	9	10	0.21	0.04	0.37
NANRC034	10	11	0.17	0.05	0.33
NANRC034	11	12	0.23	0.05	0.74
NANRC034	12	13	0.19	0.04	0.85
NANRC034	13	14	0.16	0.05	0.51
NANRC034	15	16	0.21	0.09	0.49
NANRC034	16	17	0.27	0.09	0.63
NANRC034	20	21	0.32	0.18	0.45
NANRC034	21	22	0.24	0.07	0.35
NANRC034	22	23	0.13	0.04	0.17
NANRC034	26	27	0.12	0.04	0.16
NANRC034	27	28	0.13	0.12	0.12
NANRC034	28	29	0.11	0.05	0.11
NANRC034	29	30	0.31	0.09	0.81
NANRC034	31	32	0.19	0.11	0.28
NANRC034	32	33	0.24	0.09	0.52
NANRC034	33	34	0.48	0.26	0.76
NANRC034	38	39	0.12	0.06	0.24
NANRC034	39	40	0.17	0.06	0.5
NANRC034	40	41	0.19	0.12	0.55
NANRC034	41	42	0.19	0.11	0.63
NANRC034	42	43	0.12	0.06	0.33
NANRC034	45	46	0.19	0.03	1.08
NANRC034	46	47	0.10	0.04	0.38
NANRC034	47	48	0.33	0.20	1.17
NANRC034	48	49	0.57	0.20	1.54
NANRC034	49	50	0.41	0.18	1.08
NANRC034	50	51	0.37	0.15	0.91
NANRC034	51	52	1.14	0.45	3.01
NANRC034	52	53	0.66	0.23	1.6
NANRC034	53	54	0.66	0.23	1.79
NANRC034	54	55	1.12	0.34	2.46
NANRC034	55	56	0.46	0.18	1.07
NANRC034	57	58	0.14	0.15	0.28
NANRC034	58	59	0.17	0.06	0.51
NANRC034	59	60	0.41	0.24	1.1
NANRC034	60	61	0.30	0.16	0.82
NANRC034	61	62	0.25	0.10	0.58
NANRC034	62	63	0.50	0.23	1.04
NANRC034	63	64	0.24	0.10	0.58
NANRC034	64	65	0.37	0.12	0.72
NANRC034	65	66	0.46	0.28	1.02
NANRC034	66	67	0.41	0.20	1.11
NANRC034	67	68	1.15	0.28	3.17
NANRC034	68	69	0.29	0.09	0.96
NANRC034	70	71	0.13	0.04	0.57
NANRC034	71	72	0.38	0.12	2.78
NANRC034	72	73	0.24	0.12	2.17
NANRC034	73	74	0.47	0.13	4.86
NANRC034	74	75	0.20	0.06	2.34
NANRC034	75	76	0.39	0.17	4.33
NANRC034	76	77	0.12	0.03	1.25
NANRC034	98	99	0.12	0.06	0.16

Hole ID	FROM (m)	TO (m)	Cu (%)	Au (g/t)	Ag (g/t)
NANRC034	99	100	0.18	0.10	0.32
NANRC034	100	101	0.67	0.44	1.55
NANRC034	101	102	0.16	0.04	0.69
NANRC034	102	103	0.48	0.14	1.06
NANRC034	103	104	0.27	0.06	0.67
NANRC034	104	105	0.50	0.14	1.06
NANRC034	105	106	0.10	0.02	0.23
NANRC034	106	107	0.82	0.18	1.61
NANRC034	107	108	0.66	0.13	1.2
NANRC034	108	109	1.27	0.47	2.18
NANRC034	109	110	1.05	0.26	2.14
NANRC034	110	111	0.92	0.37	1.67
NANRC034	111	112	0.43	0.13	0.75
NANRC034	112	113	0.15	0.05	0.24
NANRC034	113	114	0.38	0.12	0.61
NANRC034	121	122	0.13	0.04	0.23
NANRC034	122	123	0.22	0.09	0.36
NANRC034	123	124	0.26	0.12	0.39
NANRC034	130	131	0.27	0.06	0.59
NANRC034	131	132	0.57	0.16	0.95
NANRC034	135	136	0.50	0.14	0.83
NANRC034	136	137	0.27	0.10	0.47
NANRC034	137	138	0.38	0.09	0.65
NANRC034	138	139	1.01	0.23	1.94
NANRC034	139	140	2.27	0.62	4.21
NANRC034	140	141	0.49	0.20	0.98
NANRC034	141	142	0.83	0.25	1.65
NANRC034	142	143	1.58	0.32	3.01
NANRC034	143	144	0.59	0.23	1.19
NANRC034	144	145	0.72	0.45	1.61
NANRC034	145	146	0.54	0.18	0.99
NANRC034	152	153	0.83	0.24	1.41
NANRC034	153	154	0.37	0.11	0.68
NANRC034	154	155	0.10	0.03	0.18
NANRC034	168	169	2.83	0.93	5.58
NANRC034	169	170	0.50	0.18	1
NANRC034	170	171	0.15	0.05	0.29
NANRC034	171	172	0.20	0.19	0.49
NANRC034	172	173	4.54	1.44	7.99
NANRC034	173	174	1.57	0.44	3.07
NANRC034	178	179	0.13	0.03	0.24
NANRC034	180	181	0.13	0.05	0.34
NANRC034	213	214	0.21	0.01	0.93
NANRC034	218	219	0.14	0.03	0.35
NANRC034	230	231	0.13	0.02	0.21
NANRC034	232	233	0.74	0.20	1.39
NANRC034	233	234	0.29	0.07	0.55
NANRC034	234	235	0.17	0.08	0.32
NANRC034	235	236	0.10	0.03	0.19
NANRC034	239	240	0.12	0.04	0.24
NANRC034	240	241	0.17	0.04	0.31
NANRC034	245	246	0.62	0.18	1.19
NANRC034	246	247	0.70	0.25	1.48
NANRC034	247	248	0.69	0.40	1.35
NANRC034	248	249	0.36	0.15	0.72
NANRC034	249	250	0.84	0.42	1.56
NANRC034	250	251	0.45	0.18	0.81
NANRC034	251	252	1.03	0.24	1.78
NANRC034	252	253	0.65	0.23	1.12
NANRC034	253	254	0.35	0.13	0.54
NANRC034	254	255	0.36	0.18	0.6



Hole ID	FROM (m)	TO (m)	Cu (%)	Au (g/t)	Ag (g/t)
NANRC034	255	256	0.64	0.16	1.05
NANRC034	256	257	0.54	0.16	0.85
NANRC034	257	258	0.44	0.18	0.76
NANRC035	40	41	0.15	0.01	0.32
NANRC035	41	42	0.12	X	0.25
NANRC035	66	67	0.22	0.11	1.06
NANRC035	67	68	0.17	0.07	0.73
NANRC035	68	69	3.62	0.19	21.67
NANRC035	69	70	0.38	0.05	1.66
NANRC035	71	72	0.11	0.01	0.54
NANRC035	93	94	0.12	0.03	1.4
NANRC035	99	100	0.18	0.01	0.71
NANRC035	100	101	0.12	0.01	0.52
NANRC035	104	105	0.24	0.04	1.25
NANRC035	105	106	0.11	0.02	0.47
NANRC035	106	107	0.11	0.02	0.58
NANRC035	107	108	0.23	0.06	1.22
NANRC035	114	115	0.15	0.04	0.37
NANRC035	115	116	0.14	0.03	0.36
NANRC035	116	117	0.26	0.11	0.7
NANRC035	117	118	0.56	0.08	1.46
NANRC035	118	119	0.22	0.05	0.43
NANRC035	119	120	0.15	0.04	0.31
NANRC035	120	121	0.14	0.05	0.26
NANRC035	121	122	0.17	0.05	0.41
NANRC035	122	123	0.14	0.03	0.32
NANRC035	123	124	0.27	0.10	0.59
NANRC035	125	126	0.16	0.04	0.89
NANRC035	132	133	0.24	0.06	0.6
NANRC035	133	134	0.44	0.14	1.31
NANRC035	134	135	0.39	0.19	0.79
NANRC035	135	136	0.32	0.07	0.99
NANRC035	136	137	0.81	0.20	2.47
NANRC035	137	138	0.60	0.13	1.86
NANRC035	138	139	1.09	0.05	4.09
NANRC035	139	140	1.06	0.06	4.01
NANRC035	140	141	0.45	0.04	1.85
NANRC035	141	142	0.43	0.08	2.75
NANRC035	142	143	0.28	0.07	0.84
NANRC035	143	144	0.29	0.04	1
NANRC035	144	145	0.15	0.04	0.46
NANRC035	145	146	0.17	0.04	0.72
NANRC035	146	147	0.12	0.03	0.34
NANRC035	147	148	0.15	0.06	0.66
NANRC035	148	149	0.16	0.05	1.4
NANRC035	150	151	0.19	0.06	1.52
NANRC035	151	152	0.43	0.13	3.6
NANRC035	152	153	0.12	0.02	0.85
NANRC035	153	154	0.14	0.02	1.05
NANRC035	161	162	0.12	0.03	0.43
NANRC035	168	169	0.27	0.09	0.6
NANRC035	169	170	0.43	0.15	1.05
NANRC035	170	171	0.40	0.13	1.86
NANRC035	171	172	0.23	0.08	1.05
NANRC035	172	173	0.33	0.11	2.12
NANRC035	173	174	0.23	0.04	1.12
NANRC035	176	177	0.35	0.01	1.68
NANRC035	177	178	0.16	X	0.95
NANRC035	178	179	0.22	0.01	1.12
NANRC035	184	185	0.25	0.04	0.55
NANRC035	185	186	0.40	0.05	1.02

Hole ID	FROM (m)	TO (m)	Cu (%)	Au (g/t)	Ag (g/t)
NANRC035	186	187	0.21	0.04	0.77
NANRC035	187	188	0.69	0.31	1.83
NANRC035	188	189	0.36	0.11	0.89
NANRC035	189	190	0.29	0.08	0.71
NANRC035	190	191	0.21	0.05	0.5
NANRC035	191	192	0.33	0.09	0.68
NANRC035	192	193	0.24	0.06	0.54
NANRC035	193	194	0.32	0.05	0.67
NANRC035	194	195	0.43	0.04	0.86
NANRC035	195	196	0.24	0.06	0.51
NANRC035	199	200	0.46	0.23	0.9
NANRC035	200	201	0.34	0.11	0.64
NANRC035	201	202	0.13	0.05	0.28
NANRC035	202	203	0.18	0.07	0.3
NANRC035	203	204	0.15	0.05	0.27
NANRC035	204	205	0.20	0.08	0.35
NANRC035	205	206	0.15	0.05	0.21
NANRC035	206	207	0.23	0.04	0.36
NANRC035	207	208	0.30	0.10	0.44
NANRC035	208	209	0.26	0.10	0.39
NANRC035	209	210	1.21	0.51	1.9
NANRC035	210	211	0.83	0.28	1.52
NANRC035	211	212	0.98	0.35	1.64
NANRC035	212	213	0.32	0.12	0.49
NANRC035	213	214	0.14	0.04	0.26
NANRC035	215	216	0.13	0.03	0.25
NANRC035	216	217	0.38	0.12	0.98
NANRC035	217	218	0.59	0.13	1.46
NANRC035	218	219	0.16	0.05	0.58
NANRC035	219	220	0.26	0.08	0.7
NANRC035	223	224	0.28	0.10	0.35
NANRC035	224	225	0.22	0.06	0.29
NANRC035	225	226	0.12	0.04	0.15
NANRC035	239	240	0.11	0.04	0.13
NANRC035	240	241	3.68	0.60	6.6
NANRC035	241	242	2.49	0.30	4.59
NANRC035	242	243	2.33	0.35	3.91
NANRC035	243	244	4.17	0.18	7.17
NANRC035	244	245	1.79	1.77	3.58
NANRC035	245	246	0.76	0.15	1.31
NANRC035	246	247	0.21	0.02	0.37
NANRC035	247	248	1.54	0.14	2.45
NANRC035	248	249	0.71	0.06	1.15
NANRC035	249	250	2.63	0.10	4.33
NANRC035	250	251	1.32	0.07	2.49
NANRC035	251	252	0.52	0.09	0.93
NANRC035	252	253	0.62	0.15	1.17
NANRC035	253	254	1.74	0.50	3.04
NANRC035	254	255	0.54	0.16	1.05
NANRC035	255	256	3.80	0.83	6.76
NANRC035	256	257	0.55	0.17	1.28
NANRC035	257	258	0.32	0.09	0.85
NANRC035	258	259	0.16	0.05	0.41
NANRC035	259	260	0.36	0.10	1.12
NANRC035	260	261	0.26	0.08	0.65
NANRC035	261	262	1.13	0.25	2.49
NANRC035	262	263	0.54	0.10	1.35
NANRC035	263	264	0.12	0.02	0.31
NANRC035	264	265	0.24	0.07	0.57
NANRC035	265	266	0.36	0.07	1.04
NANRC035	266	267	0.58	0.49	1.27



Hole ID	FROM (m)	TO (m)	Cu (%)	Au (g/t)	Ag (g/t)
NANRC035	267	268	0.36	0.19	0.84
NANRC035	268	269	0.37	0.16	0.84
NANRC035	269	270	0.29	0.11	0.67
NANRC035	277	278	0.27	0.09	0.45
NANRC035	280	281	0.27	0.07	0.56
NANRC035	281	282	1.05	0.37	1.97
NANRC035	282	283	0.59	0.21	1.15
NANRC035	283	284	0.49	0.26	0.93
NANRC035	284	285	1.06	0.34	1.95
NANRC035	285	286	0.62	0.16	1.18
NANRC035	286	287	1.03	0.42	1.9
NANRC035	287	288	0.46	0.16	1.06
NANRC035	288	289	0.57	0.23	1.61
NANRC035	289	290	0.43	0.13	1.17
NANRC035	290	291	0.57	0.20	1.44
NANRC035	291	292	0.37	0.09	0.93
NANRC035	292	293	0.28	0.10	0.64
NANRC035	293	294	0.34	0.10	0.8
NANRC035	294	295	0.11	0.03	0.26
NANRC035	295	296	0.18	0.04	0.35
NANRC035	296	297	0.47	0.10	0.92
NANRC035	297	298	0.36	0.10	0.74
NANRC035	298	299	0.58	0.84	1.36
NANRC035	299	300	1.67	0.46	3.64
NANRC035	300	301	0.49	0.07	1.12
NANRC035	308	309	0.54	0.16	0.92
NANRC035	309	310	0.43	0.12	0.76
NANRC035	310	311	0.74	0.18	1.33
NANRC035	311	312	0.44	0.09	0.8
NANRC035	312	313	2.18	0.80	4.62
NANRC035	313	314	1.34	0.23	2.55
NANRC035	314	315	0.62	0.11	1.17
NANRC035	315	316	0.45	0.03	0.79
NANRC035	316	317	0.63	0.04	0.84
NANRC035	317	318	0.21	0.02	0.64
NANRC035	328	329	0.30	0.01	0.6
NANRC035	329	330	0.51	0.03	1.36
NANRC036	5	6	0.12	0.01	0.22
NANRC036	9	10	0.22	0.14	0.12
NANRC036	10	11	0.17	0.08	0.09
NANRC036	11	12	0.15	0.07	0.14
NANRC036	12	13	0.13	0.06	0.15
NANRC036	13	14	0.17	0.08	0.18
NANRC036	14	15	0.16	0.08	0.17
NANRC036	15	16	0.16	0.06	0.23
NANRC036	16	17	0.13	0.05	0.27
NANRC036	17	18	0.14	0.04	0.21
NANRC036	19	20	0.22	0.10	0.25
NANRC036	20	21	0.17	0.08	0.16
NANRC036	21	22	0.13	0.09	0.21
NANRC036	22	23	0.18	0.08	0.16
NANRC036	23	24	0.20	0.06	0.16
NANRC036	24	25	0.10	0.03	0.13
NANRC036	25	26	0.23	0.20	0.71
NANRC036	26	27	0.28	0.13	0.7
NANRC036	27	28	0.35	0.10	0.6
NANRC036	28	29	0.21	0.06	0.38
NANRC036	32	33	0.27	0.07	0.43
NANRC036	34	35	0.53	0.17	0.83
NANRC036	35	36	0.19	0.07	0.46
NANRC036	40	41	0.38	0.10	1.73

Hole ID	FROM (m)	TO (m)	Cu (%)	Au (g/t)	Ag (g/t)
NANRC036	41	42	0.37	0.11	1.01
NANRC036	42	43	0.69	0.12	1.96
NANRC036	43	44	1.71	0.42	4.71
NANRC036	44	45	0.41	0.09	1.04
NANRC036	50	51	0.17	0.08	0.49
NANRC036	51	52	0.10	0.02	0.36
NANRC036	62	63	0.12	0.03	0.79
NANRC036	67	68	0.90	0.22	2.79
NANRC036	68	69	0.50	0.13	1.37
NANRC036	69	70	0.61	0.18	1.9
NANRC036	70	71	0.76	0.25	2.26
NANRC036	85	86	0.19	0.02	0.61
NANRC036	88	89	0.81	0.17	1.85
NANRC036	90	91	0.39	0.07	1.06
NANRC036	93	94	0.20	0.05	0.38
NANRC036	105	106	0.28	0.11	0.71
NANRC036	106	107	0.29	0.09	0.51
NANRC036	107	108	0.12	0.04	0.19
NANRC036	108	109	0.60	0.22	1.04
NANRC036	109	110	0.72	0.31	1.16
NANRC036	110	111	0.54	0.19	0.92
NANRC036	125	126	0.25	0.09	0.41
NANRC036	126	127	0.24	0.06	0.41
NANRC036	127	128	0.34	0.17	0.58
NANRC036	128	129	0.51	0.20	0.84
NANRC036	129	130	0.34	0.09	0.57
NANRC036	130	131	0.13	0.06	0.2
NANRC036	131	132	0.33	0.15	0.51
NANRC036	132	133	0.48	0.18	0.82
NANRC036	133	134	0.20	0.06	0.32
NANRC036	134	135	0.37	0.17	0.57
NANRC036	135	136	0.34	0.09	0.55
NANRC036	136	137	0.36	0.13	0.67
NANRC036	137	138	0.12	0.04	0.25
NANRC036	138	139	0.83	0.18	1.46
NANRC036	139	140	0.47	0.15	0.84
NANRC036	141	142	0.17	0.03	0.36
NANRC036	142	143	0.12	0.03	0.42
NANRC036	143	144	1.34	0.30	3.52
NANRC036	144	145	0.23	0.08	0.44
NANRC036	145	146	0.40	0.16	0.8
NANRC036	146	147	0.47	0.10	0.81
NANRC036	147	148	0.88	0.19	1.54
NANRC036	148	149	0.82	0.23	1.52
NANRC036	149	150	0.35	0.14	0.63
NANRC036	150	151	0.91	0.28	1.9
NANRC036	152	153	0.20	0.04	0.41
NANRC036	154	155	0.12	0.08	0.2
NANRC036	155	156	0.12	0.06	0.17
NANRC036	158	159	0.35	0.15	0.66
NANRC036	159	160	0.51	0.19	1.09
NANRC036	160	161	0.31	0.08	0.92
NANRC036	164	165	0.19	0.01	1.17
NANRC036	167	168	0.26	0.15	0.51
NANRC036	178	179	0.16	0.03	0.41
NANRC036	181	182	0.12	0.03	0.4
NANRC036	182	183	0.19	0.05	0.4
NANRC036	183	184	0.23	0.05	0.49
NANRC036	184	185	0.10	0.02	0.26
NANRC036	186	187	0.49	0.05	1.05
NANRC036	187	188	0.22	0.03	0.56



Hole ID	FROM (m)	TO (m)	Cu (%)	Au (g/t)	Ag (g/t)
NANRC036	190	191	0.15	0.05	0.34
NANRC036	196	197	0.10	0.01	0.24
NANRC036	197	198	0.15	0.03	0.29
NANRC036	201	202	0.26	0.03	0.49
NANRC036	202	203	0.45	0.07	1.07
NANRC036	203	204	0.30	0.08	0.67
NANRC036	204	205	0.28	0.14	0.67
NANRC036	205	206	0.29	0.10	0.7
NANRC036	207	208	0.39	0.08	0.99
NANRC036	212	213	0.12	0.02	0.24
NANRC036	213	214	0.17	0.03	0.53
NANRC036	214	215	0.11	0.01	0.26
NANRC036	216	217	0.14	0.04	0.27
NANRC036	217	218	0.15	0.04	0.29
NANRC036	218	219	1.21	0.24	3.03
NANRC036	219	220	0.28	0.08	0.68
NANRC036	226	227	0.57	0.11	1.13
NANRC036	227	228	0.58	0.25	2.06
NANRC036	228	229	0.10	0.01	0.21
NANRC036	231	232	0.16	0.03	0.31
NANRC036	237	238	1.01	0.42	1.79
NANRC036	238	239	0.31	0.08	0.65
NANRC036	239	240	0.35	0.18	0.66
NANRC036	240	241	0.82	0.26	1.36
NANRC036	241	242	1.03	0.30	1.82
NANRC036	242	243	0.46	0.15	0.84
NANRC036	243	244	1.61	0.42	3.13
NANRC036	250	251	0.65	0.23	1.19
NANRC036	251	252	0.89	0.29	1.64
NANRC036	252	253	0.81	0.30	1.47
NANRC036	253	254	0.79	0.25	1.33
NANRC036	254	255	1.09	0.30	2.08
NANRC036	255	256	0.51	0.15	1.03
NANRC036	256	257	0.24	0.08	0.52
NANRC036	260	261	0.13	0.05	0.25
NANRC036	261	262	0.20	0.10	0.36
NANRC036	264	265	0.38	0.14	0.62
NANRC036	265	266	0.15	0.05	0.23
NANRC036	267	268	1.34	0.28	2.04
NANRC037	0	4	0.19	0.03	0.34
NANRC037	8	9	0.18	0.04	0.07
NANRC037	9	10	0.19	0.03	0.12
NANRC037	36	37	0.15	0.04	0.45
NANRC037	44	45	0.14	0.02	0.51
NANRC037	45	46	0.27	0.07	0.71
NANRC037	46	47	0.13	0.03	0.35
NANRC037	47	48	0.18	0.05	0.49
NANRC037	48	49	0.32	0.11	0.83
NANRC037	52	53	0.18	0.03	0.51
NANRC037	55	56	0.19	0.03	0.59
NANRC037	68	69	0.14	0.03	0.47
NANRC037	69	70	0.10	0.02	0.35
NANRC037	80	81	0.19	0.06	0.45
NANRC037	89	90	0.12	0.04	0.55
NANRC037	90	91	0.14	0.05	0.52
NANRC037	109	110	0.11	0.06	0.48
NANRC037	110	111	0.12	0.02	0.48
NANRC037	113	114	0.21	0.04	0.72
NANRC037	115	116	0.25	0.04	0.92
NANRC037	116	117	1.63	0.15	6.23
NANRC037	117	118	0.32	0.04	1.19

Hole ID	FROM (m)	TO (m)	Cu (%)	Au (g/t)	Ag (g/t)
NANRC037	122	123	0.14	0.03	0.5
NANRC037	123	124	0.14	0.04	0.42
NANRC037	124	125	0.10	0.02	0.41
NANRC037	141	142	0.17	0.06	0.34
NANRC037	157	158	0.15	0.01	0.46
NANRC037	177	178	0.19	0.05	1.34
NANRC037	178	179	0.18	0.07	1.08
NANRC037	199	200	0.18	0.08	0.63
NANRC037	207	208	0.15	0.03	0.88
NANRC037	208	209	0.34	0.10	2.15
NANRC037	209	210	0.34	0.11	2.11
NANRC037	210	211	0.33	0.06	2.21
NANRC037	211	212	0.17	0.02	0.59
NANRC037	212	213	0.25	0.11	0.82
NANRC037	213	214	0.21	0.06	0.7
NANRC037	214	215	0.11	0.06	0.42
NANRC037	215	216	0.14	0.06	0.53
NANRC037	216	217	0.15	0.05	0.62
NANRC037	218	219	0.18	0.07	0.76
NANRC037	219	220	0.35	0.11	1.88
NANRC037	223	224	0.19	0.05	0.9
NANRC037	230	231	0.13	0.05	0.66
NANRC037	231	232	0.13	0.04	0.65
NANRC037	234	235	0.11	0.05	0.51
NANRC037	235	236	0.23	0.07	0.87
NANRC037	236	237	0.49	0.10	2.08
NANRC037	237	238	0.35	0.05	1.78
NANRC037	239	240	0.15	0.07	0.64
NANRC037	240	241	0.13	0.05	0.55
NANRC037	246	247	0.24	0.04	1.2
NANRC037	269	270	0.14	0.05	0.34
NANRC037	274	275	0.17	0.07	0.48
NANRC037	275	276	0.19	0.08	0.51
NANRC037	278	279	0.26	0.19	1.41
NANRC037	279	280	0.15	0.12	0.7
NANRC037	280	281	0.45	0.12	1.41
NANRC037	281	282	0.24	0.09	0.68
NANRC037	282	283	0.76	0.22	2.14
NANRC037	283	284	0.32	0.13	0.9
NANRC037	284	285	0.93	0.21	2.5
NANRC037	285	286	0.25	0.11	0.64
NANRC037	286	287	0.22	0.09	0.56
NANRC037	287	288	0.40	0.13	1.14
NANRC037	288	289	0.47	0.14	1.42
NANRC037	289	290	0.40	0.08	1.21
NANRC037	294	295	0.71	0.15	1.41
NANRC037	295	296	0.66	0.22	1.26
NANRC037	296	297	0.56	0.19	1.07
NANRC037	297	298	0.45	0.17	0.84
NANRC037	298	299	0.35	0.11	0.74
NANRC037	299	300	0.26	0.10	0.53
NANRC037	300	301	0.22	0.12	0.42
NANRC037	301	302	0.11	0.04	0.24
NANRC037	302	303	0.18	0.06	0.4
NANRC037	303	304	0.10	0.03	0.24
NANRC037	306	307	0.10	0.03	0.29
NANRC037	307	308	2.63	0.46	6.12
NANRC037	308	309	0.59	0.14	1.2
NANRC037	309	310	0.36	0.10	0.78
NANRC037	310	311	0.36	0.10	0.69
NANRC037	311	312	1.01	0.16	1.9



Hole ID	FROM (m)	TO (m)	Cu (%)	Au (g/t)	Ag (g/t)
NANRC037	312	313	0.27	0.09	0.48
NANRC037	313	314	0.25	0.08	0.47
NANRC037	314	315	0.43	0.10	0.83
NANRC037	315	316	0.12	0.03	0.17
NANRC037	322	323	0.21	0.05	0.47
NANRC037	323	324	0.40	0.11	0.89
NANRC037	324	325	3.90	0.86	10.28
NANRC037	325	326	0.54	0.12	1.26
NANRC037	326	327	0.62	0.11	1.42
NANRC037	327	328	0.38	0.07	1.15
NANRC037	328	329	0.20	0.12	0.58
NANRC037	329	330	0.17	0.05	0.42
NANRC037	330	331	0.38	0.10	0.93
NANRC037	331	332	0.14	0.04	0.38
NANRC037	332	333	0.16	0.02	0.37
NANRC037	333	334	0.44	0.08	1.04
NANRC037	336	337	0.46	0.12	1.23
NANRC037	337	338	0.92	0.39	2.72
NANRC037	338	339	0.58	0.13	1.55
NANRC037	339	340	0.43	0.07	1.13
NANRC038	24	25	0.21	0.09	0.58
NANRC038	25	26	0.27	0.08	0.51
NANRC038	26	27	0.14	0.04	0.59
NANRC038	35	36	0.21	0.05	0.67
NANRC038	41	42	0.21	0.05	0.98
NANRC038	42	43	0.13	0.01	0.44
NANRC038	43	44	0.24	0.01	1.61
NANRC038	58	59	0.30	0.02	2.8
NANRC038	60	61	0.11	0.01	0.75
NANRC038	61	62	0.11	0.02	1.24
NANRC038	69	70	0.31	0.04	1.18
NANRC038	70	71	0.13	0.01	0.56
NANRC038	71	72	0.16	0.04	0.83
NANRC038	72	73	0.22	0.03	1.31
NANRC038	101	102	0.19	0.03	0.46
NANRC038	103	104	0.12	0.01	0.5
NANRC038	108	109	0.35	0.08	1.91
NANRC038	109	110	0.36	0.08	2.48
NANRC038	110	111	0.15	0.10	0.9
NANRC038	117	118	0.27	0.07	0.73
NANRC038	118	119	0.25	0.08	0.47
NANRC038	119	120	0.23	0.06	0.4
NANRC038	120	121	0.34	0.08	0.63
NANRC038	121	122	0.62	0.15	1.17
NANRC038	122	123	0.65	0.16	1.22
NANRC038	123	124	0.18	0.05	0.3
NANRC038	131	132	0.16	0.04	0.43
NANRC038	132	133	0.10	0.03	0.31
NANRC038	140	141	0.67	0.41	1.12
NANRC038	142	143	0.31	0.05	0.43
NANRC038	144	145	0.17	0.05	0.29
NANRC038	145	146	0.38	0.11	0.73
NANRC038	147	148	0.15	0.02	0.26
NANRC038	151	152	0.37	0.06	0.57
NANRC038	168	169	0.15	0.08	0.4
NANRC038	169	170	0.14	0.04	0.31
NANRC038	173	174	1.57	0.44	2.9
NANRC038	174	175	0.87	0.19	1.81
NANRC038	175	176	0.89	0.18	1.76
NANRC038	176	177	0.60	0.11	1.09
NANRC038	177	178	0.37	0.11	0.78

Hole ID	FROM (m)	TO (m)	Cu (%)	Au (g/t)	Ag (g/t)
NANRC038	178	179	0.33	0.08	0.95
NANRC038	179	180	0.13	0.04	0.21
NANRC038	181	182	0.19	0.04	0.36
NANRC038	182	183	1.48	0.13	3.2
NANRC038	183	184	0.67	0.07	1.62
NANRC038	185	186	0.76	0.10	3.22
NANRC038	186	187	1.10	0.25	3.61
NANRC038	187	188	0.16	0.02	0.67
NANRC038	188	189	0.48	0.12	1.95
NANRC038	189	190	0.77	0.39	2.94
NANRC038	190	191	0.41	0.11	1.73
NANRC038	191	192	0.83	0.23	2.64
NANRC038	192	193	0.22	0.03	0.96
NANRC038	193	194	0.48	0.03	1.73
NANRC038	194	195	0.51	0.04	2.29
NANRC038	195	196	0.39	0.06	2.1
NANRC038	196	197	0.26	0.05	0.68
NANRC038	197	198	0.21	0.01	0.53
NANRC038	198	199	0.11	0.03	0.34
NANRC038	199	200	0.48	0.15	1.44
NANRC038	200	201	0.73	0.25	1.98
NANRC038	201	202	0.79	0.17	2.29
NANRC038	202	203	0.48	0.12	1.39
NANRC038	203	204	0.58	0.14	1.63
NANRC038	204	205	0.53	0.15	1.53
NANRC038	205	206	0.33	0.09	0.94
NANRC038	206	207	0.62	0.07	1.32
NANRC038	207	208	0.29	0.09	0.64
NANRC038	208	209	2.05	0.25	5.15
NANRC038	209	210	1.21	0.17	3.06
NANRC038	210	211	0.57	0.08	1.43
NANRC038	211	212	0.35	0.03	0.86
NANRC038	212	213	0.74	0.11	2.04
NANRC038	213	214	0.47	0.11	1.29
NANRC038	214	215	0.25	0.08	0.78
NANRC038	215	216	0.63	0.19	1.84
NANRC038	216	217	0.28	0.08	0.75
NANRC038	217	218	0.22	0.11	0.49
NANRC038	218	219	0.46	0.19	1.17
NANRC038	219	220	0.49	0.19	1.15
NANRC038	220	221	0.41	0.16	0.99
NANRC038	221	222	0.93	0.24	1.59
NANRC038	222	223	0.62	0.27	1.13
NANRC038	223	224	1.47	1.12	2.78
NANRC038	224	225	0.99	0.38	1.92
NANRC038	225	226	0.72	0.27	1.19
NANRC038	226	227	1.32	0.31	2.61
NANRC038	227	228	0.91	0.30	1.93
NANRC038	228	229	1.02	0.27	1.83
NANRC038	229	230	0.70	0.84	1.18
NANRC038	230	231	0.87	0.33	1.39
NANRC038	231	232	0.85	0.32	1.42
NANRC038	232	233	0.98	0.42	1.59
NANRC038	233	234	0.23	0.14	0.34
NANRC038	234	235	0.96	0.34	1.48
NANRC038	235	236	0.19	0.26	0.32
NANRC038	236	237	0.94	0.31	1.63
NANRC038	237	238	0.95	0.35	1.5
NANRC038	238	239	0.60	0.31	0.93
NANRC038	239	240	0.69	0.39	1.12
NANRC038	240	241	0.13	0.05	0.2



Hole ID	FROM (m)	TO (m)	Cu (%)	Au (g/t)	Ag (g/t)
NANRC038	243	244	0.17	0.03	0.29
NANRC038	244	245	0.66	0.14	1.1
NANRC038	245	246	0.53	0.05	0.75
NANRC038	246	247	0.65	0.13	1.16
NANRC038	247	248	0.85	0.36	1.54
NANRC038	248	249	0.97	0.10	2
NANRC038	249	250	0.19	0.02	0.36
NANRC038	250	251	0.45	0.04	1.11
NANRC038	251	252	0.68	0.09	1.64
NANRC038	252	253	0.60	0.07	1.47
NANRC038	253	254	0.55	0.12	1.74
NANRC038	254	255	0.48	0.07	1.16
NANRC038	255	256	1.25	0.15	3.84
NANRC038	256	257	0.46	0.09	1.64
NANRC038	257	258	0.46	0.09	2.38
NANRC038	261	262	0.37	0.20	1.4
NANRC038	262	263	0.60	0.23	3.21
NANRC038	263	264	0.42	0.11	1.46
NANRC038	264	265	0.51	0.15	1.42
NANRC038	265	266	0.13	0.02	0.39
NANRC038	267	268	0.16	0.02	0.59
NANRC038	268	269	0.60	0.15	1.93
NANRC038	269	270	0.29	0.08	0.83
NANRC039	8	9	0.19	0.03	0.54
NANRC039	9	10	0.39	0.17	0.27
NANRC039	10	11	0.22	0.03	0.13
NANRC039	12	13	0.26	0.04	0.17
NANRC039	13	14	0.17	0.05	0.27
NANRC039	14	15	0.12	0.08	0.37
NANRC039	17	18	0.36	0.14	0.29
NANRC039	18	19	0.33	0.09	0.3
NANRC039	19	20	0.35	0.09	0.31
NANRC039	20	21	0.11	0.03	0.25
NANRC039	21	22	0.30	0.09	0.26
NANRC039	22	23	0.27	0.09	0.44
NANRC039	23	24	0.27	0.11	0.26
NANRC039	24	25	0.39	0.14	0.24
NANRC039	25	26	0.28	0.13	0.18
NANRC039	26	27	0.17	0.10	0.12
NANRC039	32	33	0.12	0.03	0.21
NANRC039	43	44	0.30	0.03	1.52
NANRC039	44	45	1.83	0.15	9.43
NANRC039	107	108	0.14	0.01	0.81
NANRC039	110	111	0.29	0.04	2.16
NANRC039	114	115	0.23	0.02	1.58
NANRC039	129	130	0.13	0.04	0.51
NANRC039	135	136	0.11	0.05	0.27
NANRC039	138	139	0.12	0.02	0.4
NANRC039	157	158	0.11	0.03	0.37
NANRC039	158	159	0.10	0.03	0.33
NANRC039	159	160	0.26	0.06	1.27
NANRC039	160	161	0.21	0.08	0.75
NANRC039	161	162	0.21	0.06	0.79
NANRC039	162	163	0.14	0.03	0.67
NANRC039	163	164	0.10	0.04	0.46
NANRC039	164	165	0.13	0.04	0.62
NANRC039	165	166	0.18	0.03	0.75
NANRC039	166	167	0.35	0.10	1.74
NANRC039	169	170	0.41	0.02	1.57
NANRC039	184	185	0.15	0.04	0.41
NANRC039	185	186	2.02	0.52	6.1

Hole ID	FROM (m)	TO (m)	Cu (%)	Au (g/t)	Ag (g/t)
NANRC039	186	187	0.45	0.12	2.34
NANRC039	187	188	0.13	0.03	0.38
NANRC039	188	189	0.45	0.15	1.31
NANRC039	191	192	0.17	0.06	0.66
NANRC039	192	193	0.30	0.06	0.9
NANRC039	193	194	0.17	0.04	0.46
NANRC039	194	195	0.15	0.11	0.36
NANRC039	196	197	0.15	0.05	0.26
NANRC039	200	201	0.25	0.07	0.58
NANRC039	201	202	0.17	0.06	0.42
NANRC039	204	205	0.12	0.03	0.33
NANRC039	207	208	0.11	0.02	0.27
NANRC039	215	216	0.20	0.03	0.57
NANRC039	216	217	0.32	0.06	0.81
NANRC039	217	218	0.48	0.13	1.59
NANRC039	218	219	0.22	0.06	0.67
NANRC039	219	220	0.71	0.12	2.41
NANRC039	220	221	0.24	0.08	1.03
NANRC039	228	229	0.19	0.07	0.31
NANRC039	231	232	0.17	0.04	0.4
NANRC039	232	233	0.25	0.07	0.4
NANRC039	233	234	0.23	0.07	0.5
NANRC039	234	235	0.32	0.08	0.76
NANRC039	235	236	1.05	0.21	3.22
NANRC039	236	237	2.18	0.43	6.89
NANRC039	237	238	0.40	0.09	1.19
NANRC039	238	239	0.17	0.07	0.45
NANRC039	240	241	0.98	0.13	2.88
NANRC039	241	242	0.22	0.07	0.65
NANRC039	242	243	0.28	0.03	0.98
NANRC039	243	244	0.17	0.03	0.51
NANRC039	246	247	0.12	0.03	0.23
NANRC039	247	248	0.13	0.05	0.32
NANRC039	248	249	0.33	0.07	1.17
NANRC039	251	252	0.34	0.02	1.49
NANRC039	252	253	0.31	0.06	1.24
NANRC039	253	254	0.21	0.05	0.63
NANRC039	254	255	0.16	0.05	0.33
NANRC039	255	256	0.45	0.09	1.32
NANRC039	256	257	0.25	0.08	0.65
NANRC039	257	258	0.96	0.12	2.74
NANRC039	258	259	0.25	0.06	0.59
NANRC039	259	260	0.26	0.06	0.66
NANRC039	260	261	0.20	0.08	0.48
NANRC039	261	262	0.33	0.06	0.78
NANRC039	262	263	0.20	0.07	0.55
NANRC039	263	264	0.24	0.07	0.56
NANRC039	264	265	0.29	0.08	0.74
NANRC039	265	266	0.43	0.19	1.18
NANRC039	266	267	0.39	0.09	1.11
NANRC039	267	268	0.22	0.08	0.59
NANRC039	268	269	0.64	0.08	1.89
NANRC039	269	270	0.18	0.03	0.67
NANRC039	279	280	0.31	0.13	0.55
NANRC039	295	296	0.59	0.12	1.83
NANRC039	296	297	0.35	0.09	0.86
NANRC039	297	298	0.20	0.05	0.51
NANRC039	300	301	0.12	0.02	0.3
NANRC039	301	302	0.73	0.23	2
NANRC039	302	303	0.37	0.08	0.94
NANRC039	303	304	0.56	0.11	1.22



Hole ID	FROM (m)	TO (m)	Cu (%)	Au (g/t)	Ag (g/t)
NANRC039	304	305	0.52	0.17	2.38
NANRC039	305	306	0.28	0.08	0.73
NANRC039	306	307	0.45	0.28	1
NANRC039	307	308	0.80	0.23	2.02
NANRC039	308	309	0.52	0.11	1.28
NANRC039	309	310	0.51	0.17	1.53
NANRC039	310	311	0.42	0.14	1.33
NANRC039	312	313	0.26	0.07	0.86
NANRC039	313	314	0.53	0.28	1.32
NANRC039	314	315	0.72	0.25	1.65
NANRC039	315	316	0.39	0.11	0.83
NANRC040	8	12	0.20	0.03	0.6
NANRC040	12	16	0.13	0.01	0.75
NANRC040	39	40	0.20	0.03	0.64
NANRC040	40	41	0.51	0.08	0.54
NANRC040	41	42	0.33	0.05	1.26
NANRC040	42	43	0.23	0.10	0.77
NANRC040	43	44	0.13	0.03	0.39
NANRC040	47	48	0.53	0.19	3.17
NANRC040	50	51	0.25	0.04	0.62
NANRC040	51	52	0.26	0.01	0.56
NANRC040	69	70	0.20	0.07	0.64
NANRC040	70	71	0.20	0.03	0.6
NANRC040	78	79	0.15	0.04	0.36
NANRC040	81	82	0.17	0.04	0.42
NANRC040	84	85	0.14	0.02	0.41
NANRC040	89	90	0.12	0.16	0.36
NANRC040	90	91	0.18	0.04	0.52
NANRC040	99	100	0.19	0.01	0.4
NANRC040	100	101	0.23	0.03	0.5
NANRC040	104	105	0.55	0.13	1.38
NANRC040	105	106	0.48	0.15	1.09
NANRC040	106	107	0.28	0.04	0.66
NANRC040	107	108	0.24	0.05	0.6
NANRC040	108	109	0.15	0.05	0.36
NANRC040	109	110	0.23	0.07	0.53
NANRC040	110	111	0.27	0.06	0.6
NANRC040	111	112	0.27	0.04	0.7
NANRC040	112	113	0.36	0.08	0.81
NANRC040	113	114	0.26	0.11	0.56
NANRC040	114	115	0.18	0.03	0.43
NANRC040	116	117	0.71	0.02	1.4
NANRC040	117	118	0.31	0.03	0.62
NANRC040	118	119	0.17	0.01	0.49
NANRC040	119	120	0.12	X	0.26
NANRC040	120	121	0.38	0.01	0.71
NANRC040	121	122	0.44	0.01	0.99
NANRC040	122	123	0.67	0.02	1.59
NANRC040	123	124	0.44	0.02	1.15
NANRC040	124	125	0.20	0.01	0.48
NANRC040	125	126	0.26	0.08	0.74
NANRC040	127	128	0.60	0.05	2.14
NANRC040	128	129	0.65	0.05	2.67
NANRC040	129	130	0.45	0.02	1.84
NANRC040	130	131	0.41	0.03	1.49
NANRC040	131	132	0.76	0.12	3.06
NANRC040	138	139	0.11	0.01	0.22
NANRC040	144	145	0.47	0.08	1.43
NANRC040	145	146	0.58	0.22	1.93
NANRC040	146	147	0.64	0.18	1.43
NANRC040	147	148	0.66	0.21	1.27

Hole ID	FROM (m)	TO (m)	Cu (%)	Au (g/t)	Ag (g/t)
NANRC040	148	149	0.87	0.39	1.95
NANRC040	149	150	1.13	0.28	2.25
NANRC040	150	151	1.48	0.32	3.62
NANRC040	151	152	1.70	0.21	3.78
NANRC040	152	153	0.78	0.12	1.72
NANRC040	153	154	0.21	0.07	0.48
NANRC040	154	155	0.10	0.02	0.28
NANRC040	155	156	0.32	0.09	0.8
NANRC040	156	157	0.33	0.08	0.88
NANRC040	157	158	0.69	0.15	1.92
NANRC040	158	159	0.40	0.08	1.11
NANRC040	159	160	0.37	0.09	0.93
NANRC040	160	161	0.26	0.17	0.56
NANRC040	161	162	0.37	0.04	0.89
NANRC040	162	163	0.16	0.03	0.54
NANRC040	163	164	1.47	0.30	6.08
NANRC040	164	165	1.89	0.33	7.68
NANRC040	165	166	1.72	1.32	5.91
NANRC040	166	167	4.22	1.59	16.92
NANRC040	167	168	1.80	0.78	6.44
NANRC040	168	169	1.02	0.32	3.26
NANRC040	169	170	0.72	0.16	2.18
NANRC040	170	171	0.42	0.09	1.61
NANRC040	171	172	0.46	0.10	1.35
NANRC040	172	173	1.01	0.46	2.61
NANRC040	173	174	0.75	0.20	2.75
NANRC040	174	175	1.04	0.25	4.63
NANRC040	175	176	0.89	0.23	4.14
NANRC040	176	177	0.54	0.16	2.5
NANRC040	177	178	0.73	0.22	3.19
NANRC040	178	179	0.21	0.04	1.03
NANRC041	30	31	0.24	0.03	0.34
NANRC041	31	32	0.27	0.02	0.33
NANRC041	32	33	0.18	0.02	0.96
NANRC041	33	34	0.31	0.07	1.66
NANRC041	34	35	0.29	0.07	2.18
NANRC041	35	36	0.31	0.06	0.86
NANRC041	36	37	0.46	0.10	0.71
NANRC041	37	38	0.19	0.01	0.56
NANRC041	38	39	0.36	0.05	1.25
NANRC041	41	42	0.14	0.03	0.47
NANRC041	42	43	0.28	0.02	0.89
NANRC041	43	44	0.27	0.01	0.82
NANRC041	44	45	0.23	0.02	0.71
NANRC041	45	46	0.25	0.03	0.56
NANRC041	46	47	0.23	0.12	0.77
NANRC041	47	48	0.22	0.02	0.64
NANRC041	48	49	0.23	0.02	0.53
NANRC041	49	50	0.14	0.02	0.29
NANRC041	50	51	0.25	0.04	0.54
NANRC041	62	63	0.26	0.04	0.46
NANRC041	63	64	0.28	0.03	0.41
NANRC041	64	65	0.30	X	0.48
NANRC041	65	66	0.45	0.05	2.22
NANRC041	66	67	0.20	0.04	0.35
NANRC041	67	68	0.31	0.04	0.52
NANRC041	68	69	0.27	0.01	0.5
NANRC041	69	70	0.30	0.02	0.57
NANRC041	71	72	0.12	0.01	0.19
NANRC041	72	73	0.16	0.07	0.39
NANRC041	73	74	0.24	0.01	0.37



Hole ID	FROM (m)	TO (m)	Cu (%)	Au (g/t)	Ag (g/t)
NANRC041	74	75	0.48	0.03	0.8
NANRC041	75	76	0.37	0.10	0.63
NANRC041	76	77	0.22	0.12	0.45
NANRC041	77	78	0.21	0.04	0.36
NANRC041	78	79	1.93	0.17	3.31
NANRC041	79	80	0.57	0.04	1.04
NANRC041	80	81	1.15	0.54	2.44
NANRC041	81	82	0.69	0.15	1.19
NANRC041	82	83	0.46	0.04	0.92
NANRC041	83	84	0.36	0.03	0.72
NANRC041	84	85	0.43	0.11	0.88
NANRC041	85	86	0.40	0.05	0.99
NANRC041	86	87	0.29	0.03	0.63
NANRC041	87	88	0.41	0.06	0.97
NANRC041	88	89	0.39	0.07	0.99
NANRC041	89	90	0.34	0.03	0.92
NANRC041	90	91	0.83	0.05	2.46
NANRC041	91	92	0.41	0.03	1.2
NANRC041	92	93	0.56	0.13	1.61
NANRC041	93	94	0.42	0.04	1.26
NANRC041	94	95	0.27	0.02	1.07
NANRC041	102	103	0.21	0.02	1.05
NANRC041	103	104	0.22	0.02	0.79
NANRC041	144	145	0.12	0.02	8.47
NANRC041	151	152	0.16	0.01	0.72
NANRC041	152	153	0.10	0.01	0.44
NANRC041	154	155	0.11	0.01	0.52
NANRC041	155	156	0.24	0.04	1.13
NANRC041	156	157	0.13	0.01	0.43
NANRC041	158	159	0.22	0.01	0.78
NANRC041	159	160	0.11	0.01	0.34
NANRC041	160	161	0.11	X	0.5
NANRC041	163	164	0.15	0.01	0.65
NANRC041	164	165	0.19	0.01	0.67
NANRC041	181	182	0.14	0.01	0.61
NANRC041	182	183	0.17	0.02	0.62
NANRC041	183	184	0.12	0.10	0.54
NANRC041	184	185	0.17	1.50	0.87
NANRC041	185	186	0.38	0.44	1.94
NANRC041	186	187	0.21	0.06	1.09
NANRC041	187	188	0.54	0.10	1.74
NANRC041	188	189	0.62	0.02	2.01
NANRC041	189	190	0.15	0.02	0.78
NANRC041	192	193	0.12	0.05	1.28
NANRC041	194	195	0.61	0.05	6.33
NANRC041	195	196	0.39	0.02	1.92
NANRC041	196	197	0.32	0.02	2.07
NANRC041	197	198	1.53	0.31	10.49
NANRC041	198	199	0.72	0.10	5.03
NANRC041	199	200	0.48	0.04	3.26
NANRC041	200	201	0.88	0.29	5.12
NANRC041	201	202	0.57	0.15	3.12
NANRC041	202	203	1.31	0.37	10.85
NANRC041	203	204	0.59	0.20	3.44
NANRC041	204	205	1.11	0.15	5.16
NANRC041	205	206	0.58	0.14	3.94
NANRC041	206	207	0.56	0.03	1.93
NANRC041	207	208	0.14	0.35	1.38
NANRC041	208	209	0.52	0.12	2.76
NANRC041	209	210	0.61	0.21	2.57
NANRC041	210	211	3.99	0.68	19.17

Hole ID	FROM (m)	TO (m)	Cu (%)	Au (g/t)	Ag (g/t)
NANRC041	211	212	4.48	2.59	24.14
NANRC041	212	213	2.18	0.87	9
NANRC041	213	214	2.54	0.74	9.92
NANRC041	214	215	0.64	0.36	2.7
NANRC041	215	216	3.01	0.53	12.22
NANRC041	216	217	2.42	0.62	9.02
NANRC041	217	218	1.35	0.24	4.79
NANRC041	218	219	1.01	0.16	3.51
NANRC041	219	220	1.15	0.27	4.85
NANRC041	220	221	0.77	0.22	4.28
NANRC041	221	222	0.44	0.29	1.86
NANRC041	222	223	1.08	0.41	4.08
NANRC041	223	224	1.17	0.32	4.47
NANRC041	224	225	1.08	0.22	4.16
NANRC041	225	226	0.60	0.21	2.25
NANRC041	226	227	0.57	0.26	2.49
NANRC041	227	228	0.18	0.19	0.68
NANRC041	228	229	0.64	0.17	2.41
NANRC041	229	230	0.90	0.10	3.57
NANRC041	230	231	1.26	0.22	5.29
NANRC041	231	232	0.78	0.16	3.71
NANRC041	232	233	0.46	0.24	3.13
NANRC041	233	234	0.63	0.27	2.93
NANRC041	234	235	0.70	0.22	3.69
NANRC041	235	236	1.08	0.36	4.71
NANRC041	236	237	1.33	0.23	7.08
NANRC041	237	238	0.99	0.38	4.64
NANRC041	238	239	0.55	0.10	2.96
NANRC041	239	240	0.66	0.12	3.12
NANRC041	240	241	0.65	0.20	2.63
NANRC041	241	242	0.50	0.14	2.14
NANRC041	242	243	0.54	0.15	2.58
NANRC041	243	244	0.65	0.11	3.16
NANRC041	244	245	0.43	0.05	2.88
NANRC041	245	246	0.16	0.01	1.07
NANRC041	248	249	0.10	0.01	1.06
NANRC041	252	253	0.51	0.04	6.46
NANRC041	253	254	0.12	0.03	1.91
NANRC041	254	255	0.45	0.02	4.86
NANRC041	255	256	0.12	0.02	1.14
NANRC041	256	257	0.11	0.01	0.91
NANRC041	257	258	0.12	0.04	0.76
NANRC041	258	259	0.36	0.01	2.27
NANRC041	259	260	0.90	0.05	4.26
NANRC041	260	261	0.47	0.08	2.17
NANRC041	261	262	0.16	0.01	0.82
NANRC041	262	263	0.31	0.07	1.51
NANRC041	264	265	0.12	0.03	0.51
NANRC041	268	269	0.11	0.04	0.42
NANRC041	269	270	0.17	0.03	0.72
NANRC041	270	271	0.14	0.05	0.63
NANRC042	10	11	0.18	0.18	0.43
NANRC042	11	12	0.41	0.02	0.6
NANRC042	12	13	0.39	0.08	0.32
NANRC042	13	14	0.32	0.18	0.45
NANRC042	14	15	0.18	0.07	0.33
NANRC042	15	16	0.21	0.05	0.32
NANRC042	16	17	0.18	0.05	0.27
NANRC042	17	18	0.15	0.22	0.35
NANRC042	18	19	0.22	0.02	0.16
NANRC042	19	20	0.14	0.01	0.29



Hole ID	FROM (m)	TO (m)	Cu (%)	Au (g/t)	Ag (g/t)
NANRC042	36	37	0.25	0.05	0.32
NANRC042	50	51	0.20	0.07	1.28
NANRC042	51	52	0.20	0.06	0.66
NANRC042	52	53	0.14	0.04	0.67
NANRC042	62	63	0.10	0.01	0.44
NANRC042	65	66	0.31	0.02	0.97
NANRC042	72	73	0.30	0.10	0.94
NANRC042	73	74	0.16	0.05	0.51
NANRC042	77	78	0.20	0.07	0.58
NANRC042	79	80	0.19	0.08	0.85
NANRC042	142	143	0.18	0.04	0.44
NANRC042	143	144	0.12	0.04	0.36
NANRC042	144	145	0.13	0.05	0.33
NANRC042	157	158	0.11	0.04	0.38

Hole ID	FROM (m)	TO (m)	Cu (%)	Au (g/t)	Ag (g/t)
NANRC042	174	175	0.22	0.03	1.11
NANRC042	175	176	0.14	0.04	0.55
NANRC042	176	177	0.21	0.05	1.46
NANRC042	177	178	0.13	0.04	0.69
NANRC042	183	184	0.13	0.04	0.63
NANRC042	184	185	0.20	0.06	0.79
NANRC042	185	186	0.34	0.10	1.33
NANRC042	186	187	0.31	0.07	1.68
NANRC042	188	189	0.17	0.05	0.99
NANRC042	189	190	0.25	0.03	1.8
NANRC042	190	191	0.16	0.01	1.46

Appendix 1: Nanadie RC and Diamond Drilling – Table 1 (JORC Code, 2012)

(Criteria in this section apply to all succeeding sections.)

Criteria	JORC Code explanation	Commentary
Sampling techniques	<i>Nature and quality of sampling (eg cut channels, random chips, or specific specialised industry standard measurement tools appropriate to the minerals under investigation, such as down hole gamma sondes, or handheld XRF instruments, etc). These examples should not be taken as limiting the broad meaning of sampling.</i>	For reverse circulation (RC) drilling, every 1m sample was cone split into clean pre-numbered calico bags from the rig-mounted cyclone/splitter and remaining sample ground-dumped mostly in rows of 30. Each 5m composite sample was collected from the relevant individual 1m sample piles with a spear and placed into a clean hand-written calico sample bag. For composite samples, proportional amounts of material were collected from each sample pile to create the composite. All sampling was undertaken by Solstice staff. Core sampling comprises half core over intervals between 0.3m to 1.2m Where field duplicates are sampled the sample comprises quarter core.
	<i>Include reference to measures taken to ensure sample representivity and the appropriate calibration of any measurement tools or systems used.</i>	A QAQC sample is inserted at a rate of 1 in 25 primary samples (Certified Reference Material or Blank QAQC sample), also field Duplicates were inserted at a rate of 1 in 25 Primary samples. Appropriate certified reference materials (CRM) were supplied by OREAS Pty Ltd and Blank material was commercially purchased clean builder's sand. Analysis of QAQC samples inserted by the Company is undertaken to monitor sample representivity and independent laboratory conditions. The CRMs used by the Company are grade and matrix matched as close as possible to interpreted geology. The laboratory (Intertek) also performed its own internal checks including insertion of pulp duplicate, standard, and repeat samples as required. Duplicate samples for RC drilling were collected at the drill site and inserted into the sample stream at a frequency of 1 in 25 Primary samples. The Duplicates were sampled directly at the drill rig along with the Primary samples, with the Duplicate samples split via cone splitter. Core sampling is from one side of the core based on an orientation line marked on the core.
	<i>Aspects of the determination of mineralisation that are Material to the Public Report. In cases where 'industry standard' work has been done this would be relatively simple (eg 'reverse circulation drilling was used to obtain 1 m samples from which 3 kg was pulverised to produce a 30 g charge for fire assay'). In other cases more explanation may be</i>	For RC drilling 1m samples were collected in a clean pre-numbered calico bag via a rig-mounted cyclone/splitter with the bulk sample collected into a plastic bucket and laid out on a cleared area of ground in rows of 30 samples. Each 1m split sample is approximately 2-3kg and representative of the metre drilled. All samples are weighed as-received by the laboratory. Each 5m composite sample is collected from each 1m sample pile over the relevant interval using a spear and proportional amounts placed into a hand-written calico sample bag to make up an approximate 2-3kg sample.



Criteria	JORC Code explanation	Commentary
	<i>required, such as where there is coarse gold that has inherent sampling problems. Unusual commodities or mineralisation types (eg submarine nodules) may warrant disclosure of detailed information</i>	Core sampling comprises half core over intervals between 0.3m to 1.2m Where field duplicates are sampled the sample comprises quarter core.
<i>Drilling techniques</i>	<i>Drill type (eg core, reverse circulation, open-hole hammer, rotary air blast, auger, Bangka, sonic, etc) and details (eg core diameter, triple or standard tube, depth of diamond tails, face-sampling bit or other type, whether core is oriented and if so, by what method, etc).</i>	The RC drilling was undertaken by an independent contractor, Core Drilling Services, using a custom-built drill rig. The drill string comprised 6m rods with a standard 5.5inch face sampling RC bit. Each hole was drilled to or near its planned depth. Each drillhole was supervised by a Solstice geologist. Diamond drilling was undertaken by independent contractor, TopDrill drilling NQ sized core to EOH from the base of each RC pre-collar.
<i>Drill sample recovery</i>	<i>Method of recording and assessing core and chip sample recoveries and results assessed.</i>	The RC sample recoveries for each metre were visually assessed by the geologist on site and estimated to be within industry acceptable standards. Moisture content (wet, dry, moist) was recorded in drill logs. Core sample recovery is determined by measuring the quantity of recovered core (after reorientation of core) against the recorded depth. Recovery is recorded in the database. Logging and measurement of recovery is currently being completed.
	<i>Measures taken to maximise sample recovery and ensure representative nature of the samples.</i>	Ground water was encountered in every hole but samples are predominantly dry. The RC drill rig utilised an onboard 350psi compressor and 1150cfm air pack, and a separate auxiliary 350psi/1150cfm booster air pack and compressor which typically provided dry and representative samples with good recovery. Core representivity was ensured by reconstructing and orienting core prior to marking a "cut line". Sampling was consistently taken from one half of the core based on the "cut line".
	<i>Whether a relationship exists between sample recovery and grade and whether sample bias may have occurred due to preferential loss/gain of fine/coarse material.</i>	No relationship appears to exist between recovery and grade and no bias is noted between assay grades and sample mass. No core grades have been reported and no sample bias determined.
<i>Logging</i>	<i>Whether core and chip samples have been geologically and geotechnically logged to a level of detail to support appropriate Mineral Resource estimation, mining studies and metallurgical studies.</i>	Geological logging was undertaken by a Solstice geologist during drilling and is considered appropriately detailed for this phase of exploration. Geotechnical logging has not been undertaken at this stage.
	<i>Whether logging is qualitative or quantitative in nature. Core (or costean, channel, etc) photography.</i>	Logging of RC drill samples included lithology, alteration, sulphide mineralisation and structural fabric, and is considered qualitative in nature. Transported cover and regolith types were also defined. The logging is considered appropriate for this phase of exploration.
	<i>The total length and percentage of the relevant intersections logged.</i>	The RC drillhole samples are logged 100% from surface to the end of hole (EOH) in detail with chip samples collected for every metre in chip trays for archive and future reference. Geological events such as bottom of transported cover, base of complete oxidation, water table, and top of fresh rock are also recorded. The logging is considered appropriate to this phase of exploration. Diamond core is logged in full, visual sulphide percentage estimates are presented in Table 1 as logged by the supervising geologist and checked by the Competent Person. Visual estimates of mineral abundance require validation via conventional assay techniques. Visual estimates are not considered a proxy or substitute for laboratory analyses where



Criteria	JORC Code explanation	Commentary
		concentrations or grades are the factor of principal economic interest. Visual estimates also potentially provide no information regarding impurities or deleterious physical properties relevant to valuations, however there are no known deleterious elements observed in the historical drill analyses.
Sub-sampling techniques and sample preparation	<i>If core, whether cut or sawn and whether quarter, half or all core taken.</i>	Sampling comprises half core over intervals between 0.3 to 1.2m. Where field duplicates are sampled the sample comprises quarter core.
	<i>If non-core, whether riffled, tube sampled, rotary split, etc and whether sampled wet or dry.</i>	The composite RC drill samples were spear sampled from piles laid out on the ground at the drill site. The majority of samples were collected dry, with very few collected wet or moist. One metre resamples are from samples collected directly from the rig-mounted cyclone/splitter and laid out with the relevant ground dumped sample. The one metre samples are collected in pre-numbered clean calico bags.
	<i>For all sample types, the nature, quality and appropriateness of the sample preparation technique.</i>	For RC drilling, one metre resamples are from samples collected directly from the rig-mounted cyclone/splitter and laid out with the relevant ground dumped sample. The samples were sent to independent laboratory, Intertek, where samples were oven dried at 100C, crushed and pulverised to 85% of total sample passing 75µm, using the SP03 or SP05 methods. The nature and quality of the sample preparation are considered appropriate. 5m composite samples were collected from unmineralised granite where identified by the geologist. Each sample was collected with a spear. These are standard industry practices for this phase of exploration.
	<i>Quality control procedures adopted for all sub-sampling stages to maximise representivity of samples.</i>	On site, field Duplicate samples are taken at a rate of 1 in 25 Primary samples based on the Company's QAQC procedures, which requires either a CRM, Blank or Duplicate be inserted in the sample stream at least every 25th Primary sample. The CRMs used by the Company are sourced from Geostats Pty Ltd and Oreas™ and are of copper and gold grade and matrix that matched as close as possible to the interpreted geology. At the laboratory stage, internal QAQC pulp duplicates are taken at a rate of 1 in 28 by Intertek. Appropriate CRM material and Control Blanks are also inserted and assessed by Intertek for internal laboratory QAQC. The QAQC Intertek inserted sample data are evaluated by Solstice's independent database manager, Core Geoscience Pty Ltd.
	<i>Measures taken to ensure that the sampling is representative of the in-situ material collected, including for instance results for field duplicate/second-half sampling.</i>	Field Duplicate samples were collected during RC drilling and inserted into the sample batches to check and ensure representivity of sample methods. Pulp repeats and element repeats for all sample types are undertaken by Intertek at the laboratory. The QAQC field inserted sample data are evaluated by Solstice's independent database manager, Core Geoscience Pty Ltd.
	<i>Whether sample sizes are appropriate to the grain size of the material being sampled.</i>	Sample mass for RC drilling of nominally 1.5–3kg for each sample is considered appropriate for the rock type and style of mineralisation. NQ half core sample sizes are appropriate for the rock type and style of mineralisation.
Quality of assay data and laboratory tests	<i>The nature, quality and appropriateness of the assaying and laboratory procedures used and whether the technique is considered partial or total.</i>	The nature and quality of the assay techniques and procedure are considered appropriate by the Competent Person. The Four Acid assay method is considered near total digest.
	<i>For geophysical tools, spectrometers, handheld XRF instruments, etc, the parameters used in determining the analysis including instrument make and</i>	No geophysical tools were used in the field in determining any element analysis.



Criteria	JORC Code explanation	Commentary
	<i>model, reading times, calibrations factors applied and their derivation, etc.</i>	
	<i>Nature of quality control procedures adopted (eg standards, blanks, duplicates, external laboratory checks) and whether acceptable levels of accuracy (ie lack of bias) and precision have been established.</i>	During drilling, field Duplicates are taken on site for samples using the same method as the Primary sample (i.e. spear/cyclone) from piles laid out on the ground or from the cyclone directly as appropriate. At the laboratory Intertek also performed internal checks including insertion of pulp duplicates, CRMs, control blanks and repeats as required. Internal screen checks are also performed to ensure the mass percent passing 75µm is consistently high. The Competent Person is satisfied acceptable levels of accuracy and precision have been established.
Verification of sampling and assaying	<i>The verification of significant intersections by either independent or alternative company personnel.</i>	Visual sulphides intersections in core being reported have been checked by experienced, senior Solstice geologists.
	<i>The use of twinned holes.</i>	No twinning of holes was undertaken.
	<i>Documentation of primary data, data entry procedures, data verification, data storage (physical and electronic) protocols.</i>	The primary lithological data for RC and diamond drilling is collected by a Company geologist in the field recording it directly into a database logging sheet on a Toughbook laptop. Data is entered into pre-defined MS Excel based log sheets following the Company's documented internal geological protocols and procedures manual. Validation measures for the field data are built into the MS Excel based log sheets. Sample logs are recorded on paper sheets in the field. Sample data is entered into the database from the sample sheets and provided to the database manager for alignment of assay data. Field data is backed-up each day with logs stored in the Company database hosted on a server. Field data is first verified by senior Company geologists and then sent electronically to Solstice's independent data management company, Core Geoscience Pty Ltd, for incorporation into a Master Database. Core Geoscience conducts several phases of field log data validation to ensure consistency and completeness. The subsequent validated and compiled dataset is exported into appropriate formats (MS Access and Micromine™) for use by Company geologists. Laboratory data is provided electronically to the Company and Core Geoscience Pty Ltd and is validated and imported by Core Geoscience into the Master Database. Data is supplied by Intertek as ASCII text file spreadsheets and PDF certificates signed by the relevant laboratory manager.
	<i>Discuss any adjustment to assay data.</i>	No adjustments have been made to any laboratory assay results.
Location of data points	<i>Accuracy and quality of surveys used to locate drill holes (collar and down-hole surveys), trenches, mine workings and other locations used in Mineral Resource estimation.</i>	The initial location of RC and diamond drill collars is recorded using a handheld Garmin GPS-Map unit with an accuracy of +/-3m, using MGA94 Zone 50 South. This method is considered appropriate for this phase of exploration drilling. Downhole surveys were conducted by trained drilling contractor personnel immediately after the completion of every RC hole using a REFLEX Sprint, North Seeking survey tool referenced to True North. No Mineral Resources Estimate work has been undertaken.
	<i>Specification of the grid system used.</i>	All drill hole data is recorded in GDA94, zone 50.
	<i>Quality and adequacy of topographic control.</i>	Past explorer Cyprum commissioned a topographic survey in February 2021 completed by Arvista Surveys. A Digital Terrain Model (DTM) was constructed using the data from the aerial survey as well as from existing drillhole surveys and adjusted where low accuracy hand-held GPS pickups created obvious anomalies in the low relief areas of the project.
Data spacing and distribution	<i>Data spacing for reporting of Exploration Results.</i>	Drillhole spacing nominally at 80x80m and 40x40m is considered by the Competent Person to be appropriate for the magmatic layered intrusive copper mineralisation being targeted at Nanadie Well.
	<i>Whether the data spacing and distribution is sufficient to establish the degree of geological</i>	Past explorer Intermin considered the data spacing 40 to 50m x 20 to 30m to be sufficient to define mineralisation to a 2004 JORC Code Compliant Inferred Resource confidence level in 2013.



Criteria	JORC Code explanation	Commentary
	<i>and grade continuity appropriate for the Mineral Resource and Ore Reserve estimation procedure(s) and classifications applied.</i>	Cyprium completed infill and extensional drilling to close the drill spacing to a nominal 25m x 25m pattern. This new closer spacing is considered to be more than sufficient to define a 2012 JORC Inferred Mineral Resource Estimate for Nanadie. No updates are being made to the Mineral Resource Estimate at this time.
	<i>Whether sample compositing has been applied.</i>	Where required, a 5m composite sample was collected from each 1m sample pile over the relevant interval using a spear and proportional amounts placed into a hand-written calico sample bag. No compositing is carried out on core samples.
<i>Orientation of data in relation to geological structure</i>	<i>Whether the orientation of sampling achieves unbiased sampling of possible structures and the extent to which this is known, considering the deposit type.</i>	Initial RAB drilling by Newcrest (1996), Dominion (1999) and Intermin (2003) was drilled on 060-240° bearing drill lines but the bulk of the subsequent drilling was drilled on east-west drill lines. The drill angle is considered adequate to test the Nanadie Well mineralisation. A number of scissor holes have also been drilled. The strike of the Nanadie Well mineralisation is north to north-northwest and the Cyprium 2020-2021 drilling pattern was designed to achieve unbiased sampling along the strike of the deposit. The horizontal to low angle nature of the oxide/supergene mineralisation was not biased by the use of vertical RC drillholes. The first two holes from the 2020-2021 diamond drill program were drilled at -60 and -80° dip angles to the west with the third hole drilled at -65° to the east and the fourth hole -63° to the east and the fifth hole drilled at -60° to the east. The regional schists and gneisses dip steeply (75°) to the east-northeast but the foliation within the layered intrusives is steep (60-80) to the west-southwest. Further, secondary sulphide veinlets are observed in drill core dipping at 50 to 60° to the northeast. Further, structural analysis is required to determine a more optimum drill angle. The Competent Person is satisfied the orientation of sampling achieved unbiased sampling of structures.
	<i>If the relationship between the drilling orientation and the orientation of key mineralised structures is considered to have introduced a sampling bias, this should be assessed and reported if material.</i>	The current understanding of the Nanadie Well Cu-Au Deposit suggests that current drill orientation has not introduced any preferential sampling bias. The primary disseminated mineralisation appears to have been remobilised into the regional fabric and now dips to the west-southwest. Remobilised secondary sulphide veins are observed in the drill core dipping to the northeast. Cross-cutting hydraulically brecciated potentially silver-rich fault structures dip to the north-northeast. Further work is required to determine the optimum drill angle and it is likely that several drill directions may be required to adequately test all the potential mineralised structural orientations at the Nanadie Well Project.
<i>Sample security</i>	<i>The measures taken to ensure sample security.</i>	Chain of sample custody is maintained by Solstice personnel. Samples were collected into plastic or calico bags which were then secured in numbered polyweave bags at the drill site. These polyweave bags were inserted into Bulka bags and then transported by Solstice staff directly to the Toll IPEC in Meekatharra for subsequent transportation to Intertek in Perth. These facilities have lockable yards to maintain security prior to sample processing. Sample submission documents listing the batch number, sample number and order number accompany the samples at each stage and are emailed directly to the laboratory managers. Samples are checked by Intertek to confirm receipt of all samples. If a discrepancy is noted, this is reported by the laboratory to Solstice.
<i>Audits or reviews</i>	<i>The results of any audits or reviews of sampling techniques and data.</i>	Internal reviews by experienced senior geologists of sampling techniques and data confirm that sampling has been conducted to industry standards.

Section 2 Reporting of Exploration Results

Criteria listed in the preceding section also apply to this section.)



Criteria	JORC Code explanation	Commentary
Mineral tenement and land tenure status	<i>Type, reference name/number, location and ownership including agreements or material issues with third parties such as joint ventures, partnerships, overriding royalties, native title interests, historical sites, wilderness or national park and environmental settings.</i>	Licences E51/1040 and M51/887 are held by Solstice as 100% owner. In addition to statutory State Government Royalties, additional royalties are payable to a syndicate comprising of W.S Hitch, K.W Wolzak, P.W Askins, and Tyson Resources PL of: • 0.735% of the revenue received from the sale of copper metal or copper in concentrate from the tenement, • 0.49% of the revenue received from the sale of any other metal, mineral or ore from the tenement.
	<i>The security of the tenure held at the time of reporting along with any known impediments to obtaining a licence to operate in the area.</i>	The licences are in good standing and there are no known impediments to renewal of the licence or to obtaining any licence to operate.
Exploration done by other parties	<i>Acknowledgment and appraisal of exploration by other parties.</i>	The area has seen extensive historical drilling, including a total of 184 historical RAB RC and/or diamond drillholes in the vicinity of the Nanadie MRE. In summary: Between 1976-1977 BHP Ltd. completed surface mapping, rock chip and soil sampling, 72 shallow 0.5 to 38m deep RAB drillholes targeting Cu, Ni & Zn and geophysical surveys. Between 1987-1993 Dominion Mining Ltd completed a total of 126 shallow RAB holes were drilled to the base of the cover and 9 shallow RC holes adjacent to historic workings to the north and south of the current MRE area. Between 1995-1996 Newcrest Mining Ltd. completed a total of 63 vertical RAB holes on 1km spaced lines with holes 300m apart on each drill line. A single fence of holes from this programme was drilled across the current Nanadie Inferred Resource that included the 23m deep discovery hole ER317-13 with 14m @ 1.2% Cu from 9m down hole. In 1999 Dominion Mining Ltd. drilled 3 fences of RAB holes across the known Nanadie deposit with holes 100m apart on section for a total of 14 drillholes. Their best results were 1m @ 0.7% Cu from holes 99NWAR009 from 8m and 99NWAR011 from 23m. In 2003, Intermin drilled 14 RAB holes that followed up the previously reported Newcrest and Dominion drill intercepts In 2004-2013 Intermin. drilled 95 RC holes 63 of which directly targeted the current Nanadie Well Inferred Resource area, the other 32 holes targeted areas outside the known MRE. During this period, they drilled 89 RAB holes of which 75 were outside the MRE area. In 2004, Intermin engaged Southern Geoscience to complete an Induced Polarisation survey at Nanadie Well. Seven lines were read on 200m section spacings north from 6994800mN. In 2006, Intermin engaged DF-EX Exploration Kalgoorlie to complete a ground magnetic survey using a GSM-19 Overhauser v7.0 total field magnetometer. In 2008, Intermin engaged GPX airborne to fly an airborne helicopter EM survey over the Nanadie Well E51/1040 for 99-line km survey using a bird mounted Geometrics G 822A Caesium vapor optically pumped magnetometer continuously sampling at 1200Hz, sensitive to 0.001nT. In 2012, Intermin commissioned Newexco to complete down hole EM surveys on 4 drill holes and a surface moving loop EM survey using an EMIT - SMARTem24 geophysical receiver. Results from 63 RC and 25 RAB (14 drilled by Intermin, 11 drilled by Newcrest and Dominion) holes were used by Intermin in the estimation of the 2004 JORC Code Compliant Inferred Resource of 36.07Mt @ 0.42% Cu & 0.064 g/t Au (Intermin, 2013).



Criteria	JORC Code explanation	Commentary
		Mithril Ltd 2013-2019. Ground geophysical surveys. 35 RC drillholes into various targets outside Nanadie Resource area including the discovery of the Stark Prospect. Mithril also drilled 5 diamond drillholes but only one hole was drilled into Nanadie Resource area in 2017. Horizon Minerals Ltd drilled 14 RC holes into the Nanadie Resource area in 2019. Between 2020-2024 Cyprum completed 84 RC holes and 7 DD holes over the Nanadie Project licences which culminated in the definition of a JORC 2012 compliant Inferred Mineral Resource Estimate of 40.4Mt @ 0.4% Cu, 0.1g/t AU and 1.0g/t Ag at a cut-off grade of 0.25% copper.
<i>Geology</i>	<i>Deposit type, geological setting and style of mineralisation.</i>	The project lies within the Yilgarn Craton and is proximal to the eastern flank of the Murchison Domain within the broader Youanmi terrane. The Nanadie Copper-Gold deposit is hosted within the Barrambie Igneous Complex (BIC) which in turn, is part of the broader Meeline suite. The BIC is interpreted to be Mesoarchaen age, circa 2810Ma, and is intruded by Neoarchaen granites and granodiorites (Ivanic et al., 2010). The BIC is a 20km long elongate mafic intrusive sill that parallels a NE-SW trending shear that marks the eastern margin of the Murchison Domain (Ivanic et al., 2010). The igneous suite is described as east facing and dipping at 75° to the east-northeast (Ivanic et al., 2010). The Nanadie Well layered intrusive is within the BIC and composed of upper greenschist facies deformed and metamorphosed gabbro, leucogabbro, anorthosites and pyroxenites. Surrounding rocks at Nanadie consist of amphibolites, sheared chlorite-quartz-muscovite schists and gneisses and granite/granodiorite intrusive bodies that flank both sides of the Nanadie Well layered intrusive as well as forming irregular granitic dykes and pegmatites that crosscut the earlier mafic intrusives. There is a thin cover generally 0.5 to 6m of Quaternary aeolian sands, soil and calcrete. The primary copper mineralisation (chalcopyrite) at Nanadie Well is associated with with pyrite, pyrrhotite and rare pentlandite and minor precious metals including gold and lesser platinum and palladium. Sulphides and precious metals have been later remobilised into the regional west-dipping shear foliation, most likely during regional folding and associated regional metamorphism. Flat lying to low angle oxide/supergene Cu/Au mineralisation occurs at the top of the current and paleo water table levels. The oxidised zone is marked mainly by iron-stained joint surfaces and some secondary Cu mineralisation dominantly malachite with lesser azurite.
<i>Drill hole Information</i>	<i>A summary of all information material to the understanding of the exploration results including a tabulation of the following information for all Material drill holes:</i> <i>• easting and northing of the drill hole collar</i> <i>• elevation or RL (Reduced Level – elevation above sea level in metres) of the drill hole collar</i> <i>• dip and azimuth of the hole</i> <i>• down hole length and</i>	See Figure 1 in body text and References.



Criteria	JORC Code explanation	Commentary
	<i>interception depth</i> <i>hole length.</i> <i>If the exclusion of this information is justified on the basis that the information is not Material and this exclusion does not detract from the understanding of the report, the Competent Person should clearly explain why this is the case.</i>	Not applicable, all information is included. The Competent Person is satisfied that drillhole information has been adequately considered, and material information has been appropriately described.
Data aggregation methods	<i>In reporting Exploration Results, weighting averaging techniques, maximum and/or minimum grade truncations (eg cutting of high grades) and cut-off grades are usually Material and should be stated.</i>	Assay grades are length-weighted. The lower cut-off grade for copper assays is 0.2% and 0.1g/t for gold. No upper cut-off grade is applied.
	<i>Where aggregate intercepts incorporate short lengths of high-grade results and longer lengths of low-grade results, the procedure used for such aggregation should be stated and some typical examples of such aggregations should be shown in detail.</i>	Aggregate intercepts reported are length-weighted. Intercepts and reported on the basis of minimum 10m interval at 0.4% copper and 5m maximum internal dilution.
	<i>The assumptions used for any reporting of metal equivalent values should be clearly stated.</i>	Metal equivalent values are not currently being reported.
<i>Relationship between mineralisation widths and intercept lengths</i>	<i>These relationships are particularly important in the reporting of Exploration Results. If the geometry of the mineralisation with respect to the drill hole angle is known, its nature should be reported. If it is not known and only the down hole lengths are reported, there should be a clear statement to this effect (eg 'down hole length, true width not known').</i>	Significant intercepts are reported as downhole lengths only.
<i>Diagrams</i>	<i>Appropriate maps and sections (with scales) and tabulations of intercepts should be included for any significant discovery being reported. These should include, but not be limited to a plan view of drill hole collar locations and appropriate sectional views.</i>	Figures in the main body of this release illustrate the Nanadie deposit mineralisation in both sectional, plan and isometric views and also indicate the variable drillhole angles and azimuths.
<i>Balanced reporting</i>	<i>Where comprehensive reporting of all Exploration Results is not practicable, representative reporting of both low and high grades and/or widths should be practiced to avoid misleading reporting of Exploration Results.</i>	All currently known significant drill assay data has been reported.
<i>Other substantive exploration data</i>	<i>Other exploration data, if meaningful and material, should be reported including (but not limited to): geological observations; geophysical survey results; geochemical survey results; bulk samples – size and method of treatment; metallurgical test results; bulk density, groundwater, geotechnical and rock characteristics; potential deleterious or contaminating substances.</i>	Other geological and geophysical work relating to Nanadie Well Project has been reported by previous operators. See ASX releases from Intermin Resources Limited (IRC), Mithril Ltd (MTH) and Horizon Minerals (HRZ). Other historical data can be located on the DEMIRS WAMEX report system. Cyprum completed an airborne magnetic and radiometric survey over the Nanadie Well E51/1040 licence in 2020. Thompson Aviation used a Cessna 210 aircraft flying at a 50m flight height to complete 3176km, 50m east-west line spaced survey. The survey used a Geometrics G822A magnetometer and a Radiation Solutions RSS00 Gamma Ray spectrometer.



Criteria	JORC Code explanation	Commentary
		Downhole EM surveys were conducted on the 2020/21 diamond drill holes at Nanadie Well and Stark in February-March 2021. The EM survey was conducted with continuous sensing tool for electromagnetic conductance anomalies with an Atlantis slim line tri-axial fluxgate magnetometer. All geophysical methods utilised have been standard practice for the generation and acquisition of geophysical data in the resources industry. Other modifying factors such as the metallurgical characteristics, potential environmental factors, hydrological conditions and geotechnical factors have not been investigated at Nanadie Well Project at this point in time. These would be considered as part of future resource updates.
<i>Further work</i>	<i>The nature and scale of planned further work (eg tests for lateral extensions or depth extensions or large-scale step-out drilling). Diagrams clearly highlighting the areas of possible extensions, including the main geological interpretations and future drilling areas, provided this information is not commercially sensitive.</i>	Further infill and extension RC drilling programmes is planned. The broader Nanadie geological model will be used to identify mineralisation trends and identify areas along strike and down dip that can be targeted for drilling. Further, diamond drilling will continue to test for high-grade zones below RC operating depths, aid structural interpretations and to allow more detailed mineralisation domain demarcation. This drill core will also provide additional core for bulk density characterisation. Metallurgical testing is planned to utilise the half core samples from current core holes. Further studies may be required depending on the outcomes of the initial sighter metallurgical test work.